Scientific Report

Niobium Nitride Thin Films deposited by High Temperature Chemical Vapor Deposition

Mercier, F

02 October 2014

The EuCARD-2 Enhanced European Coordination for Accelerator Research & Development project is co-funded by the partners and the European Commission under Capacities 7th Framework Programme, Grant Agreement 312453.

This work is part of EuCARD-2 Work Package **12: Innovative Radio Frequency Technologies (RF)**.

The electronic version of this EuCARD-2 Publication is available via the EuCARD-2 web site <http://eucard2.web.cern.ch/> or on the CERN Document Server at the following URL:
<http://cds.cern.ch/search?p=CERN-ACC-2014-0215>

Accepted Manuscript

Niobium Nitride Thin Films deposited by High Temperature Chemical Vapor Deposition

Frédéric Mercier, Stéphane Coindeau, Sabine Lay, Alexandre Crisci, Matthieu Benz, Thierry Encinas, Raphaël Boichot, Arnaud Mantoux, Carmen Jimenez, François Weiss, Elisabeth Blanquet

PII: S0257-8972(14)00822-6
DOI: doi: [10.1016/j.surfcoat.2014.08.084](https://doi.org/10.1016/j.surfcoat.2014.08.084)
Reference: SCT 19733

To appear in: *Surface & Coatings Technology*

Please cite this article as: Frédéric Mercier, Stéphane Coindeau, Sabine Lay, Alexandre Crisci, Matthieu Benz, Thierry Encinas, Raphaël Boichot, Arnaud Mantoux, Carmen Jimenez, François Weiss, Elisabeth Blanquet, Niobium Nitride Thin Films deposited by High Temperature Chemical Vapor Deposition, *Surface & Coatings Technology* (2014), doi: [10.1016/j.surfcoat.2014.08.084](https://doi.org/10.1016/j.surfcoat.2014.08.084)

This is a PDF file of an unedited manuscript that has been accepted for publication. As a service to our customers we are providing this early version of the manuscript. The manuscript will undergo copyediting, typesetting, and review of the resulting proof before it is published in its final form. Please note that during the production process errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal pertain.

Niobium Nitride Thin Films deposited by High Temperature Chemical Vapor Deposition

Frédéric Mercier^{a,b,*}, Stéphane Coindeau^{a,b,c}, Sabine Lay^{a,b}, Alexandre Crisci^{a,b}, Matthieu Benz^{a,b}, Thierry Encinas^c, Raphaël Boichot^{a,b}, Arnaud Mantoux^{a,b}, Carmen Jimenez^d, François Weiss^e, Elisabeth Blanquet^{a,b}

^a Univ. Grenoble Alpes, SIMAP, F-38000 Grenoble, France

^b CNRS, SIMAP, F-38000 Grenoble, France

^c CMTIC, Grenoble INP-CNRS, 38402 Saint Martin d'Hères, France

^d Univ. Grenoble Alpes, LMGP, F-38000 Grenoble, France

^e CNRS, LMGP, F-38000 Grenoble, France

Abstract

Synthesis of thin niobium nitride (NbN) layers by High Temperature Chemical Vapor Deposition (HTCVD) is presented and the crystallographic orientations are investigated during heteroepitaxial growth on (0001)Al₂O₃, (0001)AlN template and (11 $\bar{2}$ 0)Al₂O₃. The HTCVD NbN layers are ex-situ characterized by means of X-ray diffraction (XRD) methods, Raman spectroscopy and Transmission Electron Microscopy (TEM). Depending on the deposition temperature, hexagonal NbN or fcc (face-centered cubic) δ -NbN is obtained. Orientation relationships between the fcc δ -NbN layer with respect with the substrates are given. We discuss the role of an AlN layer as a possible protective layer of the sapphire for the synthesis of fcc δ -NbN.

Keywords: Niobium nitride, Aluminium nitride, High Temperature CVD, III-V heteroepitaxy

1. Introduction

Niobium nitride (NbN) presents excellent physical and chemical properties such as hardness, wear resistance and superconducting properties. Regarding

*Corresponding author

Email address: frederic.mercier@simap.grenoble-inp.fr (Frédéric Mercier)

its superconducting properties, NbN is a promising candidate for single-photon detectors or as a constitutive material in multilayers for superconducting radio frequency (SRF) cavities providing that NbN crystallises in the fcc structure. Among the thin film deposition techniques used for the deposition of NbN films, physical vapor deposition (PVD) methods have been almost exclusively investigated despite some attempts by chemical deposition techniques like the Chemical Vapor Deposition (CVD) technique [1, 2] and the Atomic Layer Deposition (ALD) technique [3]. Furthermore, little has been published on the orientation relationships between the NbN layer and the substrate. The most comprehensive work on orientation relationships has been done using the ALD technique [3] and the PVD technique [4, 5]. As a first step to link the structure to the resulting properties of CVD NbN layers, we present in this contribution the synthesis of thin NbN layers by High Temperature CVD and the investigations of the crystallographic orientations during heteroepitaxial growth. The HTCVD NbN layers are ex-situ characterized by means of X-ray diffraction (XRD) methods, Raman spectroscopy and Transmission Electron Microscopy (TEM).

2. Thermodynamic analysis

Thermodynamic analysis of NbN growth by HTCVD process was carried out with Factsage thermochemical software [6] using the FACT PS 6.4 thermodynamic database. NbN experiments were conducted in a quartz, cold wall, vertical CVD reactor using a two chamber reactor [7]. The first chamber is the chlorination chamber where $\text{NbCl}_{x(g)}$ species are *in situ* formed via chlorination of high purity Nb wire (99.999%) with chlorine gas $\text{Cl}_{2(g)}$ (99.999%). In the second chamber, $\text{NbCl}_{x(g)}$ reacts with $\text{NH}_{3(g)}$ (99.999%) and $\text{H}_{2(g)}$ is used as a carrier gas.

Fig. 1a shows the calculated gaseous phase formation of $\text{NbCl}_{x(g)}$ at $P=1115$ Pa by the reaction of condensed $\text{NbCl}_{2(s)}$ with $\text{Cl}_{2(g)}$ (a pre-treatment of Nb metallic wire with $\text{Cl}_{2(g)}$ is necessary to form the solid $\text{NbCl}_{2(s)}$ at high temperature and then $\text{NbCl}_{x(g)}$). At $T < 440^\circ\text{C}$, $\text{NbCl}_{5(g)}$ is the main gaseous species

while at $T > 440^\circ\text{C}$, $\text{NbCl}_{4(g)}$ is dominant. In our NbN experiments, temperature of the chlorination chamber is adjusted to preferentially form $\text{NbCl}_{4(g)}$ over $\text{NbCl}_{5(g)}$ (Fig. 1). Indeed from the thermodynamic analysis (not shown here), $\text{NbCl}_{5(g)}$ and $\text{NbCl}_{4(g)}$, in a much lower amount, react with the silica walls of the reactor to form the gaseous species $\text{SiCl}_{4(g)}$ and $\text{NbOCl}_{3(g)}$ which can lead to incorporation of oxygen and silicon in the layers. Fig. 1b gives the main gaseous species resulting from homogeneous reactions in the gas phase at $P = 1115$ Pa between $\text{NbCl}_{x(g)}$ synthesized at $T = 650^\circ\text{C}$, $\text{NH}_{3(g)}$ and $\text{H}_{2(g)}$. It indicates that $\text{NbCl}_{4(g)}$ remains the only niobium species stable for $T < 1500^\circ\text{C}$. $\text{NH}_{3(g)}$ partial pressure appears to be low which is a consequence of its dissociation into $\text{H}_{2(g)}$ and $\text{N}_{2(g)}$. In fact, due to kinetics reasons, $\text{NH}_{3(g)}$ is the most important source of N in this range of temperature [8]. Considering the heterogeneous equilibrium at this pressure and temperature range (600 - 1400°C), calculations indicate that the equilibrium condensed phase is $\text{NbN}_{(s)}$ which is the nitrogen rich Nb-N phase (no Nb_2N phase appears to be stable).

3. Experimental details

3.1. High Temperature CVD experiments

Quarters of 50.8 mm diameter Epi-ready (0001) Al_2O_3 and (11 $\bar{2}$ 0) Al_2O_3 were used as substrates. Aluminium nitride (AlN) epitaxial buffer layer with a thickness of 80 nm, grown at 1200°C on (0001) sapphire plane with (0001)[1 $\bar{1}$ 00]AlN|| (0001)[11 $\bar{2}$ 0] Al_2O_3 was also used as substrate for NbN growth. Details of preparation and characterization of the AlN layer were previously reported [7]. In the following article, this substrate will be labelled as (0001)AlN template. Substrates are set down on a 55 mm diameter non-coated graphite susceptor heated by induction. The growth temperature is measured at the center of the substrate with a dual wavelength pyrometer. Hydrogen is used as reactive carrier gas during the heating and the growth step. The reactions by-products (mainly $\text{NbCl}_{x(g)}$, $\text{HCl}_{(g)}$ and $\text{NH}_4\text{Cl}_{(g)}$) are condensed in a liquid nitrogen cold trap located prior to the pumping system. Before the deposition of NbN, niobium

metal wire is heated at 650°C under $H_{2(g)}$ atmosphere in order to partially remove any native oxide. The substrate is then heated to 1100°C under $H_{2(g)}$ (1000 cm³/min) for 10 minutes in order to remove surface contaminants. Ramp is then applied to reach the growth temperature (between 900°C and 1300°C) at a heating or cooling rate of 20°C/min. When the growth temperature is stable, the prechlorination step starts with the injection at constant rate during two minutes of pure $Cl_{2(g)}$ (1 cm³/min) or a mixture $Ar_{(g)}/Cl_{2(g)}$ ($Ar_{(g)}/Cl_{2(g)}=1.9$, with $Cl_{2(g)}$ at 1 cm³/min)). NbN deposition starts with the injection of $NH_{3(g)}$ at 40 cm³/min during 35 minutes. After the growth, the induction power is stopped and the substrate is naturally cooled down under $Ar_{(g)}$. The as-grown NbN layers were characterized without any post growth treatment.

3.2. Characterization techniques

The nature of the NbN phase of the films was studied using a PANalytical X'Pert Pro MPD two-circle diffractometer ($\theta/2\theta$, $CuK\alpha$, acceleration voltage of 45 kV and current of 40 mA from a sealed X-Ray tube) equipped with a 1D linear detector. Samples were measured in an asymmetric configuration in order to remove the contribution of the sapphire substrate and the eventual AlN layer. The orientation relationships between individual phases of the films and the single crystalline substrates were determined using non coplanar in-plane diffraction measurement and pole figures were acquired by applying the In-plane measurement technique with a Rigaku Smartlab five-circle diffractometer ($CuK\alpha$, acceleration voltage of 45 kV and current of 200 mA, from a rotated anode generator).

Raman spectra were recorded both using a Jobin-Yvon T64000 confocal Raman spectrometer and a Renishaw RM1000 System at room temperature. The samples were excited using a 514 nm line from an Ar⁺ gas laser with a power of approximately 5 mW on the sample. Micro sampling was accomplished with a 100x objective (numerical aperture of 0.9) for the T64000 and with a 50x for the RM1000 (numerical aperture of 0.75). RM1000 spectrometer is equipped with a notch filter cutting low frequency around 150 cm⁻¹. Due to is

triple subtractive configuration, T64000 spectrometer allows measurement at low frequency, less than 20 cm^{-1} . Only spectra acquired from the RM1000 are shown in this paper. All the peaks below 200 cm^{-1} were confirmed with the T64000 spectrometer.

The samples for the TEM observation were first mechanically ground to a thickness of $25\text{ }\mu\text{m}$ and then polished to a mirror-like state with diamond discs of 9, 3 and $1\text{ }\mu\text{m}$. Samples were finally ion-milled (Model PIPS, Gatan) under a condition of 10 kV until a hole was made, followed by a condition of 4 kV during 30 minutes. A conventional 300 kV JEOL3010 microscope was used to examine these samples.

The samples were also analyzed by Electron probe micro-analysis (EPMA) using a Cameca SX50 at accelerating voltages of 5 kV, 7 kV, 10 kV and 12 kV. The Nb $L\alpha$, Al $K\alpha$, O $K\alpha$, C $K\alpha$ and N $K\alpha$ characteristic X-ray peaks were analyzed. Layers composition and thicknesses were calculated using the Stratagem software (SAMx, France) and a $\Phi(\rho.z)$ calculation model.

4. Results and discussion

4.1. Common features of NbN layers

The NbN_x layers present a homogenous specular surface with a metallic reflection from silver color (hexagonal NbN) to gold color (cubic NbN). The layers exhibit no visible cracks under the optical microscopy.

Typical thicknesses are 39 nm (which corresponds to a growth rate of 67 nm/h) and 49 nm (84 nm/h) for the samples grown at 900°C and 1300°C respectively, determined by X-Ray reflectometry. In those conditions, it has been observed that the growth rate does not depend on the substrate.

By EPMA analysis, we found that the Nb/N atomic ratio varies between 0.95 and 1.06, which means that almost stoichiometric NbN is obtained. Carbon atomic content below 5% is typically obtained. It indicates partial etching of the graphite susceptor during the deposition process leading to incorporation of carbon in the films. Oxygen atomic content varies in a much broader range

from 2% to a maximum nominal composition of $\text{Nb}_{0.49}\text{O}_{0.3}\text{N}_{0.49}$ (samples corresponding to this composition are not presented in this contribution). The origin of such high oxygen incorporation could result from an uncontrolled etching of the silica walls or an eventual oxidation of the Nb metallic charge.

4.2. Phase analysis

In the Nb-N phase diagram, five different crystallographic structures are admitted [1, 4, 9] : α -Nb (Nb with interstitial N), hexagonal close-packed (hcp) β - Nb_2N , tetragonally distorted face-centered cubic (fcc) γ - Nb_4N_3 , fcc δ -NbN, and hcp ϵ -NbN (anti-WC structure, $P\bar{6}m2$). An additional hexagonal phase δ' -NbN with the space group $P6_3/mmc$ is supposed to occur during the transformation of ϵ -NbN towards δ -NbN. In our study, we observe basically two phases, i.e. the hexagonal NbN and fcc δ -NbN.

Fig. 2 gives the typical $\theta/2\theta$ X-ray diffraction pattern of layers deposited at 900°C and 1300°C. At 1300°C, the NbN layer shows a cubic structure ($Fm\bar{3}m$) with a highly (111) preferential orientation (ICDD: 01-088-2404 with $a=0.444$ nm). Additional peaks are detected indicating inclusions of hexagonal phase ($2\theta=32.4^\circ$) together with a small polycrystalline contribution as proved by the presence of the (200) and the (220) reflections. Additionally, the log scale plot clearly shows that the (111) reflection peaks are asymmetric. The origin of this feature is still uncertain, but it could be a signature of an additional oxygen-containing phase like $\text{NbN}_{0.9}\text{O}_{0.1}$ ($Fm\bar{3}m$, ICDD: 00-025-1360).

At 900°C, the NbN layer has a hexagonal structure with a highly (000 l) preferential orientation. Additional peaks are observed which reveal a small polycrystalline contribution as indicated by the (10 $\bar{1}$ 0) and the (10 $\bar{1}$ 1) reflections. However due to the similarities of XRD patterns for δ' -NbN (ICDD: 04-004-3003) and ϵ -NbN (04-004-3002) for the obtained orientations, it is difficult to conclude about the nature of the hexagonal phase. We noticed that addition of argon in the chlorination chamber ($\text{Ar}_{(g)}/\text{Cl}_{2(g)}=1.9$) leads to the stabilization of oriented ϵ -NbN (the (10 $\bar{1}$ 1) peak observed at 38.6° is characteristic of ϵ -NbN), Nb_2N (ICDD: 01-075-1616) and Nb_4N_3 (ICDD: 01-089-6041).

This observation is in disagreement with our thermodynamic calculations which show that only NbN is stable. However, Singer also found that addition of Ar_(g) in the gas phase during PVD leads to the stabilization of Nb₂N [10].

The Raman spectra help to identify the nature of the NbN layers (Fig. 3). For the sample grown at 1300°C, the low frequency domain located at ~154 cm⁻¹ and the high frequency nitrogen band at ~510 cm⁻¹ clearly indicate δ-NbN [11, 12]. For the sample grown at 900°C in presence of Ar_(g) during the chlorination step, the peaks at ~370 cm⁻¹ and ~674 cm⁻¹ are typical of the ε-NbN phase. The low frequency domain around 182 cm⁻¹ and 225 cm⁻¹ indicates the presence of Nb₂N and Nb₄N₃ [11]. This findings are consistent with the XRD 2θ results and confirm the presence of ε-NbN. However, the sample grown at 900°C presents a low intensity Raman signal without any matching with the ε-NbN spectra of Kaiser [11]. One peak at ~178 cm⁻¹ is detected which can not be clearly related to ε-NbN and might indicate δ'-NbN. Finally, no band centered at ~ 650 cm⁻¹ is observed in all of our layers which reveals the absence of a crystallized Nb₂O₅ phase [13, 14].

4.3. Orientation relationships of δ-NbN

In this part, the effect of substrate orientation is studied. Three δ-NbN layers have been grown on (0001)Al₂O₃, (0001)AlN template and (11 $\bar{2}$ 0)Al₂O₃ at 1300°C under the same process conditions. In all cases, θ/2θ diffraction scans show an out of plane (111) preferred orientation for all cases (Fig. 4).

A convenient parameter for defining the degree of preferred orientation of f.c.c. films is the *f* factor, which is calculated as [15]

$$f = \frac{(R_m - R_c)}{(1 + R_m)} \quad (1)$$

in which *R_m* is the measured background corrected intensity ratio of the (111) to the (200) peak, i.e. I(111)/I(200), and *R_c* is the expected value of *R_m* for a completely random distribution of crystallites (*R_c* = 1.37). *f* will approach 1 as the (111) planes become preferentially oriented parallel to the substrate surface. A high degree of preferred orientation is found for all the δ-NbN layers, with

$f=0.98, 0.99, 0.92$ respectively for NbN deposition on (0001)Al₂O₃, (0001)AlN, (11 $\bar{2}$ 0)Al₂O₃.

Despite this high degree of preferred orientation, additional orientations and phases are observed depending on the substrate. Compared with the δ -NbN layer grown on (0001)Al₂O₃, the NbN layer grown on (0001)AlN shows reduced (100) and (110) orientations but presents a hexagonal contribution as attested by the 000l peaks of hexagonal NbN. The δ -NbN layer grown on (11 $\bar{2}$ 0)Al₂O₃ shows a higher contribution of the (10 $\bar{1}$ 0) orientation but no hexagonal NbN is detected.

In order to investigate if the δ -NbN is fiber textured or epitaxially grown, non coplanar in-plane diffraction scans and pole figures were measured (Fig. 5 and Fig. 6). Fig. 5 shows the in-plane orientation relationship of δ -NbN on (0001)Al₂O₃ and (0001)AlN. We found $\langle 11\bar{2} \rangle \delta\text{-NbN} \parallel \langle 11\bar{2}0 \rangle \text{Al}_2\text{O}_3$ (equivalent to $\langle 1\bar{1}0 \rangle \delta\text{-NbN} \parallel \langle 10\bar{1}0 \rangle \text{Al}_2\text{O}_3$) and $\langle 11\bar{2} \rangle \delta\text{-NbN} \parallel \langle 10\bar{1}0 \rangle \text{AlN}$ (equivalent to $\langle 1\bar{1}0 \rangle \delta\text{-NbN} \parallel \langle 11\bar{2}0 \rangle \text{AlN}$). We also note that the hexagonal NbN detected in the layer grown on (0001)AlN also have an orientation relationship which is $\langle 10\bar{1}0 \rangle \text{hexagonal NbN} \parallel \langle 10\bar{1}0 \rangle \text{AlN}$. In Fig. 6a, pole figures of δ -NbN on (0001)Al₂O₃ reveals the presence of two in-plane variants as attested by the six fold symmetry in the 111 and 220 pole figures. These two twin domains are related by a 180° rotation around the [111] axis, which double the expected three fold symmetry. In-plane relationships are thus $[1\bar{1}0] \delta\text{-NbN} // [10\bar{1}0] \text{Al}_2\text{O}_3$ and $[\bar{1}10] \delta\text{-NbN} // [10\bar{1}0] \text{Al}_2\text{O}_3$. Such two in-plane variants have already been observed in NbN films on (0001)Al₂O₃ grown by by ALD [3] and by PVD [4]. However, six peaks exist at $\alpha=71^\circ$, positioned between the main 111 peaks (the angle between a main 111 peak and a secondary peak is $\beta=18.7 \pm 0.1^\circ$). On the 220 pole figure of Fig. 6b, 18 peaks exist at $\alpha=90^\circ$; the six main peaks are separated by 60° between two main peaks and $\alpha=18.7 \pm 0.1^\circ$ between the main peak and a secondary peak. The origin of these peaks is still uncertain but as a first step to understand this feature, we give on Fig. 6d, the 111 and 220 pole figures of a thicker δ -NbN layer grown on (0001)Al₂O₃. This 200 nm thick layer also presents the two in-plane variants. Additionally, twinned grains with a

(511) orientation parallel to the (0001)Al₂O₃ are observed. The angle between the [511] direction and the [111] direction is $\alpha=39^\circ$. This type of twinning is typical and occurs in a cubic systems [16]. A comparison of Fig. 6a and Fig. 6d shows that the additional peaks do not correspond to the 511 twinned grains despite the same azimuthal orientation ($\beta=18.7 \pm 0.1^\circ$). The peaks observed on Fig. 6a could represent the beginning and the transition towards the appearance of 511 twinned grains. This feature needs further investigation. The FWHM (Full Width at Half Maximum) of NbN(111) and NbN(220) are 2.1° and 1.3° indicating a significant mosaicity which can origin from an important lattice mismatch between NbN and Al₂O₃. The mosaicity does not decrease with the thickness but it should be noted that the 49 nm thick layer presents less diffusion around the 111 and 220 peaks compared with the 200 nm thick sample.

In Fig. 6b, the pole figure indicates that the CVD of NbN on (0001)AlN resulted also in cubic (111) oriented film with two in-plane variants. No additional peaks are observed. However, on the 111 pole figure, low intensity and diffuse peaks appear at the same azimuthal direction than the 111 peaks. They have been attributed to a small contribution of the (100) hexagonal NbN. The FWHM of NbN (111) is 1.8° indicating also a significant mosaicity of NbN. Despite a low lattice mismatch between (111)NbN and (0001)AlN ($\epsilon=-0.12\%$, see next section), such high FWHM is likely a consequence of the twinned structure and the presence of a secondary phase. In Fig. 6c, the δ -NbN layer grown on (11 $\bar{2}$ 0)Al₂O₃ presents more complex pole figures, revealing an in-plane disorder.

TEM observations of cross sections given on Fig. 7 and Fig. 8 show that NbN layers are composed of grains with a lateral size of 150 nm. Selected area diffraction patterns (SAED) on individual grains confirms the presence of the two variants for both substrates. By SAED we notice that two adjacent grains can belong to the same variant. Single domains area can extend up to 1 μ m laterally. Voids are detected at the NbN/(0001)Al₂O₃ interface. Peeling of the NbN layer is observed only for the layer grown directly on (0001)Al₂O₃. The observed bending reveals a tensile stress in the NbN layer. This point is

addressed in the following section.

Fig. 9 illustrates the top and side views of atomic arrangements between the two possible variants of δ -NbN with respect with the (0001) plane of Al_2O_3 and the (0001) plane of AlN. In Table 1, we summarize the epitaxial relationships between the NbN layer and the substrates found by XRD and TEM observations.

4.4. Role of AlN layer on residual stress in NbN layers

In heteroepitaxial systems, the final observed stress in the crystal is the sum of the extrinsic stress due to the thermal expansion mismatch between the crystal and substrate and the intrinsic stresses which develop during the growth. These intrinsic stresses originate in the lattice mismatch between epilayer and substrate as well as in the process of grain coalescence which occurs in the early stages of growth. We have already shown that the growth of thin AlN layers (<500 nm) leads to tensile stress at room temperature [17]. We discuss in this part the influence of the AlN template on the stress in NbN by comparing generated strain for the NbN grown on (0001) Al_2O_3 and for the NbN grown on (0001)AlN template. The epitaxial mismatch in the case of NbN on sapphire is

$$\epsilon = 100 \times \frac{d_{sub} - d_{layer}}{d_{layer}} \quad (2)$$

with $d_{layer}=1.5 \times d(112\text{NbN})=0.2665$ nm and $d_{sub}=d(11\bar{2}0\text{Al}_2\text{O}_3)=0.2379$ nm the d-spacing of the corresponding planes. It leads to a compressive state in the NbN layer with $\epsilon_{epi}=-11\%$. In such high epitaxial mismatch system, introduction of periodical misfit dislocations will permit a partial relaxation [18]. A Fourier filtered image of a NbN on (0001) Al_2O_3 observed by HRTEM [19] indicates a 9-8 relationship. In that case, the epitaxial mismatch induced strain is

$$\epsilon = 100 \times \frac{9 \times d_{sub} - 8 \times d_{layer}}{8 \times d_{layer}} \quad (3)$$

with gives a compressive state with $\epsilon=-0.42\%$.

For NbN deposited on (0001)AlN template, $d_{sub}=d(10\bar{1}0\text{AlN})=0.2695$ nm and the NbN layer is in a tensile state with $\epsilon=0.12\%$. This low epitaxial mismatch induced strain does not generate misfit dislocations. The strain generated

by grain coalescence can be estimated by the model of Nix and Clemens [20]

$$\epsilon = \left[\frac{2(\gamma_{sv} - \gamma_{gb})}{L} \frac{1 - \nu}{E} \right]^{1/2} \quad (4)$$

where E is the elastic modulus, and γ_{sv} and γ_{gb} are the surface and grain boundary energies, respectively and L , the size of islands before coalescence. By using orders of magnitude for parameters of eq 4 with typically $2\gamma_{sv} - \gamma_{gb} \sim 1$ J/m², $E/(1-\nu) \sim 400$ GPa, $L \sim 50$ nm, it leads to a tensile state with $\epsilon \sim 1\%$ [21, 22]. Detailed measurements of the stress during the growth should help to clearly evaluate the island coalescence induced stress and the difference between NbN on sapphire and NbN on AlN since misfit strain and dislocations can alter or enhance the nucleation in a complex way [23]. Finally, the thermal stress contribution can be calculated from the elastic properties of the materials and from the evolution of the coefficients of thermal expansion (CTEs) with temperature. We used the equations and the formalism of Hsueh [24] to calculate the thermal strain in NbN/Al₂O₃ and NbN/AlN/Al₂O₃. CTE has been replaced by its integral with respect to the temperature taken for NbN [25], AlN and Al₂O₃ [26]. For a ΔT of -1275°C (-875°C) corresponding to a growth temperature of 1300°C (900°C) and a cooling to 25°C, the calculated thermal strain in the NbN layer is $\epsilon = 0.32\%$ (0.21%) indicating a tensile state. From the calculations, the AlN layer does not change the magnitude and the sign of the strain. With the assumption that island coalescence generates a similar stress for NbN on Al₂O₃ and NbN on AlN, the NbN layer will be at room temperature in a tensile state with a residual strain within the order of magnitude of the island coalescence induced strain. NbN on AlN will be in a more tensile state. The peeling observed for NbN/Al₂O₃ (Fig. 7) and not observed for NbN/AlN can be explained by the thermal instability of sapphire in H_{2(g)} at $T > 1200^\circ\text{C}$ [7]. Etching of sapphire will create voids at the NbN/Al₂O₃ during the heating step and the nucleation of NbN. On the contrary, AlN remains stable under H_{2(g)} at high temperature and acts as a protective layer for sapphire. Despite a slightly higher residual tensile state in the NbN/AlN, the absence of voids at the interface will not induce peeling.

5. Conclusion

In this paper, we have experimentally investigated the High Temperature CVD growth of NbN on Al_2O_3 and on $\text{AlN}/\text{Al}_2\text{O}_3$ substrates. Depending on the deposition temperature, hexagonal NbN or fcc δ -NbN can be obtained. The layers are highly oriented with an in-plane orientation relationship with (0001) Al_2O_3 and (0001)AlN. The growth on (11 $\bar{2}$ 0) Al_2O_3 leads to more in-plane disorder. For the (0001) oriented substrates, the use of an AlN thin layer (80 nm thick) leads to a better crystallinity of the δ -NbN but generates some ϵ -NbN grains. No peeling is observed when the sapphire is protected with an 80 nm thick AlN layer. This work demonstrated that the HTCVD technique is a promising route for the synthesis of high quality NbN epitaxial thin layers. Further work is currently in progress to improve the crystal quality of the films and to link the growth conditions to the superconducting properties.

Acknowledgement

This study was partly supported by EuCARD-2 project (Enhanced European Coordination for Accelerator Research & Development). S.C. would like to thank P. Gergaud for discussions on (511) twinned grains observed in pole figures. F. M. would like to thank R. Martin for performing the EPMA characterization and F. Robaut for her valuable comments on the EPMA analysis.

References

- [1] G.-i. Oya, Y. Onodera, Transition temperatures and crystal structures of single crystal and polycrystalline NbNx films, *Journal of Applied Physics* 45 (3) (1974) 1389–1397.
- [2] A. Kafizas, C. J. Carmalt, I. P. Parkin, CVD and precursor chemistry of transition metal nitrides, *Coordination Chemistry Reviews* 257 (13) (2013) 2073–2119.

- [3] J. A. Klug, N. G. Becker, N. R. Groll, C. Cao, M. S. Weimer, M. J. Pellin, J. F. Zasadzinski, T. Proslier, Heteroepitaxy of group IV-VI nitrides by atomic layer deposition, *Applied Physics Letters* 103 (21) (2013) 211602.
- [4] S. Lloyd, D. Tricker, Z. Barber, M. Blamire, Growth of niobium nitride/aluminium nitride trilayers and multilayers, *Philosophical Magazine A* 81 (10) (2001) 2317–2335.
- [5] R. Espiau de Lamaestre, P. Odier, J.-C. Villégier, Microstructure of NbN epitaxial ultrathin films grown on A-, M-, and R-plane sapphire, *Applied Physics Letters* 91 (23) (2007) 232501–232501.
- [6] Factsage, FACTSAGE Thermodynamic Equilibrium Software, version 6.4, GmbH, Aachen, Germany, 2001.
- [7] R. Boichot, N. Coudurier, F. Mercier, S. Lay, A. Crisci, S. Coindeau, A. Claudel, E. Blanquet, M. Pons, Epitaxial growth of AlN on c-plane sapphire by high temperature hydride vapor phase epitaxy: Influence of the gas phase N/Al ratio and low temperature protective layer, *Surface and Coatings Technology* 237 (2013) 118–125.
- [8] R. Boichot, N. Coudurier, F. Mercier, A. Claudel, N. Baccar, A. Milet, E. Blanquet, M. Pons, CFD modeling of the high-temperature HVPE growth of aluminum nitride layers on c-plane sapphire: from theoretical chemistry to process evaluation, *Theoretical Chemistry Accounts* 133 (1) (2014) 1–13.
- [9] V. Ivashchenko, P. Turchi, E. Olifan, Phase stability and mechanical properties of niobium nitrides, *Physical Review B* 82 (5) (2010) 054109.
- [10] I. Singer, R. Bolster, S. Wolf, E. Skelton, R. Jeffries, Abrasion resistance, microhardness and microstructures of single-phase niobium nitride films, *Thin Solid Films* 107 (2) (1983) 207 – 215.

- [11] R. Kaiser, W. Spengler, S. Schick Tanz, C. Politis, Raman spectra and superconductivity of various phases of a high-Tc superconductor: NbN, *physica status solidi (b)* 87 (2) (1978) 565–573.
- [12] X.-J. Chen, V. V. Struzhkin, S. Kung, H.-k. Mao, R. J. Hemley, A. N. Christensen, Pressure-induced phonon frequency shifts in transition-metal nitrides, *Phys. Rev. B* 70 (2004) 014501.
- [13] C. Constable, J. Yarwood, P. Hovsepian, L. Donohue, D. Lewis, W.-D. Münz, Structural determination of wear debris generated from sliding wear tests on ceramic coatings using Raman microscopy, *Journal of Vacuum Science & Technology A* 18 (4) (2000) 1681–1689.
- [14] J. M. Jehng, I. E. Wachs, Structural chemistry and Raman spectra of niobium oxides, *Chemistry of Materials* 3 (1) (1991) 100–107.
- [15] E. F. Skelton, S. A. Wolf, T. L. Francavilla, Structural characterization of NbCN thin films, *Journal of Vacuum Science & Technology* 18 (2) (1981) 259–261.
- [16] E. Weiss, E. Kedar, N. Mainzer, The formation of twins in 111 HgCdTe grown by travelling heater method and their effect on device quality, *Journal of Crystal Growth* 132 (12) (1993) 191 – 199.
- [17] M. Pons, R. Boichot, N. Coudurier, A. Claudel, E. Blanquet, S. Lay, F. Mercier, D. Pique, High temperature chemical vapor deposition of aluminum nitride, growth and evaluation, *Surface and Coatings Technology* 230 (2013) 111–118.
- [18] T. Kehagias, P. Komninou, G. Nouet, P. Ruterana, T. Karakostas, Misfit relaxation of the AlN/Al₂O₃ (0001) interface, *Physical Review B* 64 (19) (2001) 195329.
- [19] M. Guziewicz, A. Laszcz, J. Domagala, K. Golaszewska, J. Ratajczak, R. Kruszka, M. Juchniewicz, A. Czerwinski, W. Słysz, Structural anal-

- ysis of epitaxial NbTiN films, in: Electron Technology Conference 2013, International Society for Optics and Photonics, 2013, pp. 89022S–89022S.
- [20] W. Nix, B. Clemens, Crystallite coalescence: A mechanism for intrinsic tensile stresses in thin films, *Journal of Materials Research* 14 (08) (1999) 3467–3473.
 - [21] E. Etzkorn, D. Clarke, Cracking of GaN films, *Journal of Applied Physics* 89 (2) (2001) 1025–1034.
 - [22] B. Wu, J. Bai, V. Tassev, M. L. Nakarmi, W. Sun, X. Huang, M. Dudley, H. Zhang, D. Bliss, J. Lin, et al., Stress evolution during the early stages of AlN vapor growth, in: Materials Research Society, Symposium Proceedings, Vol. 892, Cambridge Univ Press, 2006, p. 653.
 - [23] H. Brune, K. Bromann, H. Röder, K. Kern, J. Jacobsen, P. Stoltze, K. Jacobsen, J. No, et al., Effect of strain on surface diffusion and nucleation, *Physical Review B* 52 (20) (1995) R14380.
 - [24] C.-H. Hsueh, S. Lee, H.-Y. Lin, Analyses of mode I edge delamination by thermal stresses in multilayer systems, *Composites Part B: Engineering* 37 (1) (2006) 1–9.
 - [25] X.-G. Lu, M. Selleby, B. Sundman, Calculations of thermophysical properties of cubic carbides and nitrides using the Debye–Grüneisen model, *Acta materialia* 55 (4) (2007) 1215–1226.
 - [26] R. R. Reeber, K. Wang, Lattice parameters and thermal expansion of important semiconductors and their substrates, in: MRS Proceedings, Vol. 622, Cambridge Univ Press, 2000, pp. T6–35.
 - [27] W. Chen, J. Jiang, Elastic properties and electronic structures of 4d-and 5d-transition metal mononitrides, *Journal of Alloys and Compounds* 499 (2) (2010) 243–254.

List of Figures

- 1 (a) Calculated partial pressure of gaseous species vs. temperature
for the reaction between $\text{NbCl}_{2(g)}$ and $\text{Cl}_{2(g)}$ at $P=1115$ Pa. (b)
Main species in the gas phase between reaction of $\text{NbCl}_{x(g)}$ with
 $\text{NH}_{3(g)}/\text{H}_{2(g)}$ mixture.
- 2 $\theta/2\theta$ X-ray diffraction pattern of layers deposited at 900°C and
 1300°C . The linear scale (a) indicates a preferred orientation for
all samples. The log scale (b) clearly shows the small contribution
of the additional phases and orientation
- 3 Raman spectra of NbN layers, for different growth conditions.
The deduced phases are indicated.
- 4 $\theta/2\theta$ X-ray diffraction pattern of 49 nm δ -NbN layers grown at
 1300°C on different substrates. ZB-NbN stands for the Zinc-
Blende structure (space group : F-43m). ZB-NbN is a metastable
phase and remains hypothetical [27].
- 5 Determination of the in-plane orientation relationships by non
coplanar in-plane diffraction measurements for NbN deposited at
 1300°C on the sapphire substrate and on the AlN template. The
first order appears with less intensity than the second order due
to geometrical reasons in the diffractometer.
- 6 Pole figures of δ -NbN layers grown. (a) 49 nm δ -NbN on (0001) Al_2O_3 .
(b) 49 nm δ -NbN on (0001)AlN template. (c) 49 nm δ -NbN
(11 $\bar{2}$ 0) Al_2O_3 . (d) 200 nm δ -NbN on (0001) Al_2O_3 . On 111 pole
figures of (a), (b) and (d), peaks of (10 $\bar{1}$ 4) Al_2O_3 and (11 $\bar{2}$ 6) Al_2O_3
are visible due to the resolution of the diffractometer.
- 7 Observation of a cross-section of the 49 nm δ -NbN layer on (0001) Al_2O_3 .
Selected area diffraction pattern reveals the presence of the two
variants.
- 8 Observation of a cross-section of the 49 nm δ -NbN layer on (0001)AlN
template. Selected area diffraction patterns reveal the presence
of the two variants.
- 9 Crystallographic relation between the (0001) plane of Al_2O_3 , the
(0001) plane of AlN the two possible variants of δ -NbN layer.

Fig. 1: (a) Calculated partial pressure of gaseous species vs. temperature for the reaction between $\text{NbCl}_{2(g)}$ and $\text{Cl}_{2(g)}$ at $P=1115 \text{ Pa}$. (b) Main species in the gas phase between reaction of $\text{NbCl}_x(g)$ with $\text{NH}_3(g)/\text{H}_2(g)$ mixture.

Fig. 2: $\theta/2\theta$ X-ray diffraction pattern of layers deposited at 900°C and 1300°C. The linear scale (a) indicates a preferred orientation for all samples. The log scale (b) clearly shows the small contribution of the additional phases and orientation

Fig. 3: Raman spectra of NbN layers, for different growth conditions. The deduced phases are indicated.

Fig. 4: $\theta/2\theta$ X-ray diffraction pattern of 49 nm δ -NbN layers grown at 1300°C on different substrates. ZB-NbN stands for the Zinc-Blende structure (space group : F-43m). ZB-NbN is a metastable phase and remains hypothetical [27].

Fig. 5: Determination of the in-plane orientation relationships by non coplanar in-plane diffraction measurements for NbN deposited at 1300°C on the sapphire substrate and on the AlN template. The first order appears with less intensity than the second order due to geometrical reasons in the diffractometer.

Fig. 6: Pole figures of δ -NbN layers grown. (a) 49 nm δ -NbN on (0001) Al_2O_3 . (b) 49 nm δ -NbN on (0001)AlN template. (c) 49 nm δ -NbN (11 $\bar{2}$ 0) Al_2O_3 . (d) 200 nm δ -NbN on (0001) Al_2O_3 . On 111 pole figures of (a), (b) and (d), peaks of (10 $\bar{1}$ 4) Al_2O_3 and (11 $\bar{2}$ 6) Al_2O_3 are visible due to the resolution of the diffractometer.

Fig. 7: Observation of a cross-section of the 49 nm δ -NbN layer on (0001) Al_2O_3 . Selected area diffraction pattern reveals the presence of the two variants.

Fig. 8: Observation of a cross-section of the 49 nm δ -NbN layer on (0001)AlN template. Selected area diffraction patterns reveal the presence of the two variants.

Fig. 9: Crystallographic relation between the (0001) plane of Al_2O_3 , the (0001) plane of AlN the two possible variants of δ -NbN layer.

List of Tables

- 1 Orientation relationships between NbN layers and (0001) oriented substrates

Film	Substrate	Orientation
δ -NbN	(0001)Al ₂ O ₃	(111)[1 $\bar{1}$ 0]//(0001)[10 $\bar{1}$ 0] (111)[$\bar{1}$ 10]//(0001)[10 $\bar{1}$ 0]
δ -NbN	(0001)AlN	(111)[1 $\bar{1}$ 0]//(0001)[11 $\bar{2}$ 0] (111)[$\bar{1}$ 10]//(0001)[11 $\bar{2}$ 0]
hexagonal NbN	(0001)AlN	(0001)[11 $\bar{2}$ 0]//(0001)[110 $\bar{2}$ 0]

Table 1: Orientation relationships between NbN layers and (0001) oriented substrates

- NbN thin layers were grown by High Temperature CVD
- Heteroepitaxial growth of hexagonal phase and single phase cubic fcc NbN layers were obtained depending on temperature
- Crystallographic orientations between fcc NbN and (0001)Al₂O₃, (0001)AlN template and (11 $\bar{2}$ 0)Al₂O₃ are given
- We discuss the role of an AlN layer as a possible protective layer of the sapphire for the synthesis of fcc δ -NbN