CERN-ISR-VA 76-41
C2

EUROPEAN ORGANISATION FOR NUCLEAR RESEARCH

CERN-ISR-VA/76-41

Closed distribution

Document for CERN
PRIVATE COMMUNICATION
not to be quoted or copied without author's permission

THE EFFECT OF CLEANING AND OTHER SURFACE TREATMENTS ON THE
SURFACE COMPOSITION OF TECHNOLOGICAL MATERIALS*

by

A.G. Mathewson

CERN LIBRARIES, GENEVA

CM-P00064840

Geneva, 8th October 1976

*
Invited paper to be presented at the
International Symposium on Plasma Wall Interaction
at the Institut für Plasmaphysik, Jülich,
18-22 October 1976.

ABSTRACT

Methods of producing atomically clean surfaces applicable to technological materials and large vessels where the surface area may attain tens or hundreds of square metres are described.

The efficiency of treatments such as in situ glow discharge cleaning with different gases or heating to high temperature in vacuo are investigated by means of Auger Electron Spectroscopy, Electron and Ion Induced Gas Desorption and Discharge Induced Pressure Bump Analysis. In addition, the binding energies of CO on some stainless steels was measured by Flash Desorption.

The materials investigated include Cu, Al, Ti, 316 L + N stainless steel, Inconel 600 and Inconel 625.

INTRODUCTION

The vacuum system of the Intersecting Storage Rings (ISR) at CERN, Geneva, is essentially a 2 km long, 160 mm diameter stainless steel tube in which, after baking at 300°C for 24 hours, the average pressure is $\approx 8 \times 10^{-12}$ torr (N_2 equivalent) of which $\approx 95\%$ is H_2 , the rest being CO, CO_2 and CH_4 . When the ISR is in operation the interior walls of the vacuum chamber are subjected to ion bombardment which desorbs adsorbed surface gas which may result in large increases in pressure detrimental to the running of the machine (Calder [1]). Thus such a low average base pressure in no way implies that the vacuum system is completely clean. It only means that the binding energies of the remaining adsorbed surface gases are high enough to give a low thermal outgassing at room temperature and that the pumping speed of the installed pumps is high enough (and, of course, their vacuum limit low enough) to maintain this low pressure. It was these ion induced pressure increases which prompted us at CERN to investigate our stainless steel surface, identify the adsorbed surface gases and try to find ways of removing them.

In this review paper on the effect of cleaning and other surface treatments on the surface composition of technological materials, I shall describe the methods of investigating surfaces which we have used and also the techniques we have developed for removing adsorbed surface gas. I shall not be talking about cleaning procedures for single crystals of pure Ni or W with surface areas of a few square mm but methods applicable to large vessels fabricated from polycrystalline multi-component alloys such as Inconel 600 or 316 L + N stainless steel whose surface areas may, as in the case of the ISR, extend to hundreds of square metres.

TESTING OF CLEANING METHODS

Before describing some cleaning methods we must first define what is meant by a clean surface. We may adopt the definition of Allen [2] which states that an atomically clean surface is one which is free of all but a few per cent of a single monolayer of foreign atoms either absorbed on or substitutionally replacing surface atoms of the parent lattice. Alternatively we may define a clean surface to be one which desorbs less than a certain number of gas molecules per incident electron or ion. Depending on the circumstances and the degree of cleanliness required, the maximum tolerable number of gas molecules desorbed must be specified as must the energy of the bombarding particles and the ion species. In the testing of the cleaning methods we shall describe, one or both of these definitions shall be used.

The composition of the surface may be conveniently analysed using Auger Electron Spectroscopy (A.E.S.) (Palmborg et al. [3]). By means of A.E.S. the elements present in the first 3 or 4 monolayers of the surface may be identified. In addition to identification, A.E.S. provides a quantitative measurement since for up to one monolayer coverage the Auger peak height is proportional to the surface coverage of the element in question. The advent of the cylindrical mirror analyser and the publication of standard spectra of the elements (Palmborg et al. [4]) enables fast and easy elemental analyses of surfaces to be made.

The efficiency of the cleaning method in reducing the surface coverage of adsorbed gas may be checked by subjecting the cleaned surface to electron and/or ion bombardment and measuring the number of desorbed surface gas molecules per incident electron or ion.

An apparatus in which this can be done is shown schematically in Figure 1, a fuller description may be found in publications by Achard [5] and Mathewson [6]. In this equipment samples can be subjected to electron, K^+ and $^{15}N_2^+$ ion bombardment with energies up to 3 keV and the number and identity of the desorbed gas molecules determined.

AN S.E.M. PICTURE OF SURFACES

Before describing some cleaning methods it is interesting and useful to have a visual picture of the surface to be cleaned. This can be achieved using a Scanning Electron Microscope (S.E.M.).

In Fig. 2 (top) are reproduced the S.E.M. photographs of the surface of Inconel 600 (left) and Inconel 625 (right). On the second row (left) is an S.E.M. photograph of 316 L + N stainless steel. It is seen that the Inconel 600 surface is extremely rough and jagged. The Inconel 625 and 316 L + N stainless steel surfaces, however, exhibit single grains between 10 and 20 μ in diameter with the grain boundaries apparently having been etched away leaving micron-sized holes and crevices. During manufacture of plates of these alloys the materials were hot rolled with the resulting formation of a thick scale or oxide layer which was subsequently removed by pickling or chemical etching. It is this pickling which is responsible for the structure of the Inconel 600 surface and for the preferential etching of the grain boundaries on the Inconel 625 and 316 L + N stainless steel surfaces.

Heating the 316 L + N stainless steel to 950°C in vacuo for 6 hours produced the surface shown in Fig. 2 (second row, right). The individual grains have grown in size and the grain boundaries less distinct. However, some cracks and crevices still remain.

Glass bead vapour blasting - a process in which small glass beads in a water jet are directed at the surface - produced the surface shown in Fig. 2 (third row, left). This is a sample of Inconel 625 whose surface was originally in the same state as that shown in Fig. 2 (top, right). The surface is rough in appearance with numerous holes and cracks. The alloy surface under the action of the particle bombardment of the vapour blasting tends to flow plastically and the fissures and etched grain boundaries tend to get covered up thus trapping any contamination they may contain.

The S.E.M. photograph in Fig. 2 (third row, left) shows the surface of an aluminium alloy (Antico 100) which had been "cleaned" by essentially both an acidic and an alkaline etching solution. The surface appears porous with numerous small holes - potential sources of contamination.

A CHEMICAL SOLVENT PRECLEANING PROCEDURE

In all cases before final cleaning all materials must be subjected to a precleaning to remove gross contamination such as oil and grease and particulate matter of all types. Such a procedure never provides an atomically clean surface (Barton and Govier [7]) since traces of the cleaning solutions will always remain and, of course, exposure to air results in adsorption of water vapour, CO₂, etc.

A reasonably effective precleaning procedure used at CERN consists of the following steps :

- (a) Perchloroethylene (C₂Cl₄) vapour degreasing (121°C)
- (b) Ultrasonic cleaning in alkaline detergent (pH = 11)
- (c) Rinsing in cold, demineralized water
- (d) Drying in a hot air oven at 150°C.

There are, of course, a multitude of similar procedures using other chlorinated and fluormated hydrocarbons such as trichlorethylene and freon, and alcohols. The above process we have found to be effective in precleaning pure Ti, Ti alloy (73 Ti 13 V 11 Cr 3 Al), Inconel 600, Inconel 625, Cu and 316 L + N stainless steel.

The efficiency of the above precleaning procedure may be checked by A.E.S. In Fig. 3 (top) is shown the Auger spectrum from a previously uncleaned 316 L + N stainless steel specimen. The surface is heavily contaminated with C (≈ 82 at.%). From the peak shape the C appears to be in the form of graphite (Haas et al. [8]) but oil and other complicated hydrocarbons are certainly also present on the uncleaned surface. Traces of S, Cl, Ca and Na are observed. The underlying Fe, Cr and Ni the main constituents of 316 L + N stainless steel are obscured by this contaminating layer. The O is not necessarily an impurity but is an essential component of the stainless steel passivation layer, however it must be

remembered that O from adsorbed H_2O , CO and CO_2 will also contribute to the observed O peak.

The second spectrum from the top in Fig. 3 shows the result of only degreasing a similar uncleaned 316 L + N stainless steel sample in perchlorethylene vapour. The C contamination is greatly reduced (≈ 44 at. %) revealing the underlying Fe, Cr and Ni. However, traces of S, Ca and Na still remain, K is not removed and Cl from the vapour degreasing process is evident.

Passing an uncleaned 316 L + N sample through all four stages of the precleaning procedure results in the Auger spectrum second from the bottom in Figure 3. The C contamination is further reduced (≈ 28 at. %) but still vastly in excess of the bulk C content (0.016% by weight). Some Ca is still present on the surface but the S, Cl and Na are now barely detectable. The Cu - not a constituent of 316 L + N stainless steel and hence a true contaminant - which appeared on the surface, was traced to the detergent bath. It was due to manual rubbing of the surface of some Cu parts with an abrasive cloth while still in the detergent bath resulting in some Cu remaining in suspension in the detergent.

The bottom spectrum of Fig. 3 illustrates the necessity of using demineralised water in the rinsing stage of the cleaning process. If ordinary tap water is used, as in this case, appreciable quantities of Ca (≈ 36 at. %), the origin of which is most likely $CaCO_3$, are observed on the surface.

CLEANING BY HEATING

Atomically clean surfaces of high melting point metals may be easily obtained by heating the material to a high temperature in vacuum. This method is only applicable to those materials whose surface contaminants possess higher vapour pressures than the base material or decompose at temperatures below the melting point of the base metal. However, at elevated temperatures there exists the possibility that the surface impurities may not leave as gaseous species but instead diffuse into the bulk. Alternatively impurities in the bulk may diffuse to the surface. In addition, the mechanical properties of the material may be seriously degraded by the high temperature treatment.

The effect on the surface composition of heating Inconel 600 to high temperature is shown by the series of Auger spectra in Fig. 4. The surface composition was analysed at room temperature ($25^\circ C$) and after heating at $100^\circ C$ intervals from $100^\circ C$ to $900^\circ C$. The spectra were recorded with the sample at room temperature after heating for one hour. The sample had been precleaned by the method described above before mounting in the Auger system. The corresponding quantitative surface concentrations of C, O, N, Cr and S calculated from these spectra are shown in Fig. 5.

The composition of the Inconel 600 surface after the precleaning is shown by the top spectrum of Fig. 4. The major contaminants were C (≈ 18 at. %), Ca (≈ 16 at. %) with traces of Cl (≈ 2 at. %). Again the O is not considered to be a true contaminant but is a

normal component of the metal surface which had, of course, been exposed to air and hence oxidized. There was $\approx 33.5\%$ O on the surface after the precleaning. The underlying alloy components (Ni, Cr, etc.) were partly obscured since the surface layer of C, Ca and O prevented the escape of their Auger electrons.

Heating from 25°C to 600°C produced relatively little change in the surface composition of the Inconel 600 as seen via A.E.S. There was a gradual decrease in the O peak height and an increase in the C peak height to between 40 and 60 at. %, the Ni remaining relatively constant. From 300°C the Cr peak became evident.

Heating to 700°C , 800°C and 900°C produced the most dramatic change in the Auger spectra. The O surface concentration dropped sharply from 700°C eventually being undetectable at 900°C . The C peak was just visible at 900°C .

Because of the disappearance of the overlying C and O, the Ni and Cr peaks became more apparent from 600°C . The low energy Ni peak at 61 eV which, because of the low energy of the Auger electron, is extremely sensitive to overlying material, was clearly visible at 800°C and 900°C .

From 600°C upwards the S surface concentration increased rapidly. This is S which has diffused from the interior of the alloy and segregated at the surface. After heating to 900°C for 1 hour there was ≈ 13 at. % S on the Inconel 600 surface. Also at 800°C and 900°C traces of P (≈ 2 at. %) were observed.

A similar set of measurements for Inconel 625 and Ti have been reported by Achard and Mathewson [9] and Mathewson [10] respectively.

A set of six samples (two of 316 L + N stainless steel, two of Ti alloy and two of pure Al) were precleaned following the procedure described above - the pure Al, however, was only vapour degreased - and mounted in the electron and ion desorption system shown in Fig. 1. The efficiency of the precleaning and the effect of 200°C and 300°C bakeouts for 6, 12, 18 and 24 hour periods was controlled by measuring the number of desorbed surface gas molecules per incident $2\text{ keV }^{15}\text{N}_2^+$ ion. This quantity we call the desorption coefficient η .

A measurement of η was made after mounting the samples in the desorption system. The system was then baked for, say, six hours at 300°C and η was measured again. To test the effect of a 12 hour 300°C bakeout completely new specimens were used since it is not obvious that two 6 hour bakeouts give the same result as one 12 hour bakeout.

For all three materials investigated before and after bakeout, bombardment by $2\text{ keV }^{15}\text{N}_2^+$ ions produced significant desorption of only four gases, H_2 , CH_4 , CO and CO_2 . Figures 6 and 7 show the desorption coefficients η for the four species desorbed from Ti before and after 6, 12, 18 and 24 hour bakeouts at 300°C and 200°C respectively.

For all three materials the results were similar. There was a wide scatter in the measured η 's before bakeout due, it is believed, to non reproducibility of the precleaning conditions. It must be remembered that the samples were not precleaned under controlled laboratory conditions but were treated as normal pieces of vacuum equipment and passed

through the normal industrial precleaning baths and thus are hopefully representative of actual vacuum chambers.

A 300°C, 24 hour bakeout of Ti, Al and 316 L + N stainless steel is sufficient to reduce both η_{CO} and η_{CH_4} to less than 0.1 mol. ion⁻¹ but both η_{H_2} and η_{CO} remain high ≈ 1 mol. ion⁻¹. Bakeouts of shorter times give somewhat higher η values. Total η 's of the order of 5 mol. ion⁻¹ were measured.

A 200°C bakeout is less efficient with all η 's correspondingly higher. Both η_{H_2} and η_{CO} were ≈ 3 to 4 mol. ion⁻¹ after 24 hours at 200°C with $\eta_{\text{CO}_2} \approx 0.8$ mol. ion⁻¹ and $\eta_{\text{CH}_4} \approx 0.2$ mol. ion⁻¹. Total η 's ≈ 9 mol. ion⁻¹ were measured.

On unbaked samples total η 's ≈ 20 mol. ion⁻¹ were measured.

In general η_{H_2} and η_{CO} are ≈ 10 times η_{CO_2} and η_{CH_4} irrespective of bakeout temperature or time and are thus the major contributors to pressure instabilities in systems subjected to ion bombardment.

Desorption coefficients are functions of both the mass and the energy of the bombarding ion. Thus the values given above are only valid for 2 keV $^{15}\text{N}_2^+$ (mass 30) ions. The energy dependence of η for $^{15}\text{N}_2^+$ ions is shown in Fig. 8.

A fuller description of these and other measurements will be found in the publication by Mathewson [6].

In general, electron induced desorption coefficients are less than ion induced desorption coefficients. In Fig. 9 are shown the electron and K⁺ ion induced desorption coefficients for OFHC Cu after precleaning and after bakeout at 300°C for 24 hours (Achard [5]). The bombardment energy was 1.4 keV. It can be seen that before and after bakeout for ion bombardment η_{H_2} and η_{CO} are of the same order of magnitude followed by η_{CO_2} and η_{CH_4} . For the electrons the order is somewhat different. Before bakeout $\eta_{\text{CO}_2} > \eta_{\text{H}_2} > \eta_{\text{CO}} > \eta_{\text{CH}_4}$, and after bakeout $\eta_{\text{H}_2} \gg \eta_{\text{CO}} \approx \eta_{\text{CO}_2} > \eta_{\text{CH}_4}$. Before bakeout for electron bombardment total η 's ≈ 2 mol. electron⁻¹ were measured and ≈ 0.14 mol. electron⁻¹ after bakeout. For ion bombardment the corresponding figures were ≈ 22 mol. ion⁻¹ and 7 mol. ion⁻¹ respectively.

The ratio of the ion and electron induced desorption coefficients at 1.4 keV $\left(\frac{\eta_{\text{K}^+}}{\eta_{\text{e}^-}}\right)_{1.4 \text{ keV}}$ are given for 316 L + N stainless steel, pure Cu and pure Ti in Table I before and after 300°C, 24 h bakeout.

GLOW DISCHARGE CLEANING

Under the action of ion bombardment, adsorbed surface gas and also metal atoms may be removed by sputtering. Argon is the gas most commonly used because of its inertness and thus inability to react chemically with the surface bombarded. In addition, the higher mass of Ar relative to He and Ne makes the sputtering more efficient (Carter and Colligon [11]). The use of the heavier inert gases Kr and Xe is excluded only on account of their cost.

Ion bombardment of a surface disrupts it greatly and introduces a large number of defects. This, however, is of minor consequence in the cleaning of large vacuum vessels where defects in the surface layers are not necessarily detrimental to their operation. However, some ions will always be implanted in the surface and, after the discharge cleaning has terminated, will tend to diffuse to the surface and desorb thermally providing a source of gas which has to be coped with by the system pumps. This effect can be minimized by degassing the discharge cleaned vessel at as high a temperature as possible for some hours after the end of the discharge.

For investigation of the discharge cleaning process a miniature 316 L + N stainless steel discharge cell was placed in the A.E.S. system. As shown in Fig. 10 a 316 L + N stainless steel specimen could be rotated from its position integral with the discharge cell wall to a position suitable for analysis via A.E.S. without breaking the vacuum. Thus the cleaning effect of the argon ion bombardment could be monitored in situ after various ion doses. The discharge cell was not deliberately heated but the energy transferred from the discharge to the cell raised its temperature to about 100°C.

The Auger spectrum in Fig. 11 (top) shows the state of the specimen, i.e. the chamber wall before discharge. Both cell and specimen had been subjected to the precleaning process described above. The main contaminant is C with some Ca, S and Cu.

The bottom spectrum is taken from the discharged specimen after an argon ion dose of 1.6×10^{19} ions cm^{-2} . Further doses did not change the spectrum. One can now clearly see the base constituents of the steel such as Fe, Cr, Ni, Mo and even N_2 . However, some C is still present but in the form of carbide shown by the characteristic peak shape (Haas et al. [8]). The O peak has greatly diminished and the low energy Fe and Ni peaks are very strong indicating that very little overlying contamination is present.

In addition to surface gas the stainless steel itself is sputtered and all insulators and windows in such a discharge become coated with a layer of metal. However, because of the geometry, i.e. radial ion bombardment, the sputtered material is not removed from the chamber but is merely transported from side to side with only the volatile components being removed. Carbon itself is not volatile and is therefore not completely removed for this reason.

The effect of introducing 10% oxygen into the argon gas used in the discharge is spectacular (Lambert and Comrie [12]). Apart from some implanted argon and, of course, some oxygen, an atomically clean surface free of C is obtained after a dose of only 1×10^{18} ions cm^{-2} compared to 1.6×10^{19} ions cm^{-2} with pure argon which even then did not remove all the C. The before and after argon/10% oxygen discharge Auger spectra are shown in Fig. 12. The effect of the oxygen is obviously to oxidise the surface C forming CO and CO_2 which is then pumped from the system.

During the pure argon discharge cleaning of the ISR vacuum chambers, it was observed that even after baking a vacuum chamber at 400°C for 27 hours the initiation of the discharge in the vacuum chamber always resulted in a distinct rise in pressure ($\Delta P \approx 5 \times 10^{-2}$ torr at a

base pressure of 1×10^{-2} torr of argon). Thus the argon ions are desorbing gases which have low desorption rates at 400°C namely large binding energies. Analysis of these discharge-induced pressure rises would give some useful information concerning what was being desorbed from the vacuum chamber surface and in addition could be used for testing the stability of different surfaces under ion bombardment and the efficiency of different cleaning methods including the discharge itself.

The equipment for analysis of the gas discharge induced pressure rises is shown in Fig. 13. A more complete description is given in the publication of Calder et al [13].

It was found that discharge cleaning with the chamber at 300°C was more efficient than at room temperature. The composition and time dependence of a typical pressure rise are shown in Fig. 14 for a 316 L + N stainless steel test chamber at 300°C . The only gaseous species desorbed are CO , H_2 , CH_4 and CO_2 . The relative surface concentrations of these gases were obtained from Fig. 14 by integrating each curve with respect to time but for CO stopping the integration when the desorption coefficient $\eta = 0.01 \text{ mol. ion}^{-1}$. It was found that 1.6 torr ℓ of gas were desorbed which corresponded to ≈ 17 monolayers and that 99.75% of the desorbed gas consisted of CO , the rest being H_2 , CO_2 and CH_4 . After an ion dose of $4.5 \times 10^{17} \text{ ions cm}^{-2}$, the discharge and the bakeout were stopped. The test chamber was de-mounted and stored in air in the laboratory for 4 weeks, then remounted in the analysis equipment. The result of a second argon discharge at 300°C is shown in Fig. 15. Again CO and H_2 were desorbed but in much smaller quantities. The peak ΔP was $\approx 2 \times 10^{-4}$ torr and only 1.1×10^{-4} torr ℓ were desorbed in total. Even after several exposures to air followed by 300°C bakeouts, the recontamination level was always of the same order as that shown in Fig. 15.

Pure argon discharge induced desorption from Ti and Al chambers gave essentially the same results as those obtained for stainless steel. The main component desorbed was again CO followed by H_2 , CO_2 and CH_4 in essentially similar quantities as found on stainless steel.

To reduce the thermal outgassing of implanted argon the temperature of the argon discharge cleaned ISR 316 L + N stainless steel vacuum chambers is raised from 300°C (the temperature at which the discharge is carried out) to 350°C (if of course the chamber design permits) for about 10 hours. The argon thermal degassing rate at 300°C just after discharge was $\approx 9.0 \times 10^{-12} \text{ torr } \ell \text{ s}^{-1} \text{ cm}^{-2}$, $\approx 1.2 \times 10^{-13} \text{ torr } \ell \text{ s}^{-1}$ at 300°C but after 10 hours at 350°C and $< 1 \times 10^{-15} \text{ torr } \ell \text{ s}^{-1} \text{ cm}^{-2}$ at room temperature after 10 hours at 350°C .

The effect on the desorption coefficients η of an in situ pure argon discharge in an unbaked system on an Al sample is shown in Fig. 16. The argon discharge reduced η_{H_2} , η_{CH_4} , η_{CO} and η_{CO_2} to less than $0.01 \text{ mol. ion}^{-1}$ but left an $\eta_{\text{Ar}} \approx 0.3 \text{ mol. ion}^{-1}$ which is a total η more than an order of magnitude lower than can be achieved with a 24 hour, 300°C bakeout. An argon ion dose $\approx 8.3 \times 10^{17} \text{ ions cm}^{-2}$ was required.

An in situ pure N_2 discharge in an unbaked system proved unsuccessful with η for mass 28 (CO and N_2) of the order of 2 to 3 mol. ion^{-1} for Ti, Al and 316 L + N stainless steel even after an ion dose of $1.6 \times 10^{18} \text{ ions cm}^{-2}$ but nevertheless reduced η_{H_2} , η_{CH_4} and η_{CO_2}

to below $0.01 \text{ mol. ion}^{-1}$. As shown in Fig. 17 for 316 L + N stainless steel, a subsequent pure argon discharge reduced the mass 28 desorption coefficient but left each sample with an η_{Ar} between 0.15 and $0.4 \text{ mol. ion}^{-1}$.

Analysis of a N_2 discharged 316 L + N stainless steel specimen produced the Auger spectra of Fig. 16. A large surface concentration of N_2 was revealed ($\approx 45 \text{ at. \%}$) which was certainly the source of the mass 28 desorbed.

The effect of a pure argon discharge on 2 keV electron and K^+ ion induced desorption coefficients is shown in Fig. 19 for pure Al. After an argon ion dose of $8.5 \times 10^{17} \text{ ions cm}^{-2}$, η_{H_2} , η_{CH_4} , η_{CO} and η_{CO_2} were all $\approx 0.01 \text{ mol. ion}^{-1}$ and $\approx 0.1 \text{ mol. ion}^{-1}$ for argon with K^+ ion bombardment. Under electron impact all desorption coefficients including argon were $\approx 0.001 \text{ mol. electron}^{-1}$ (Achard [5]).

FLASH DESORPTION

The binding energies of surface species may be measured by the technique of flash desorption in which a sample of say, stainless steel is heated in vacuo at a known rate and the partial pressures of the gases released during the flash recorded. The temperatures at which pressure peaks in this desorption spectrum occur are related to the binding energy of the desorbed species. The measurement of these binding energies is of interest since it can be seen whether increasing bakeout temperatures from 300°C to perhaps 350°C or 400°C will significantly deplete the populations of the more tightly bound surface states.

The theory of flash desorption is well covered in the literature (Redhead [14]) so only the final expression from which the binding energies may be calculated will be given. The relationship between the binding energy E and the temperature T_p at which the maximum desorption occurs is given by

$$\frac{E}{kT_p^2} = \frac{\nu}{\beta} \exp\left(\frac{-E}{kT_p}\right)$$

where k is Boltzmann's constant

ν is the rate constant ($\approx 10^{13} \text{ s}^{-1}$)

and β is the rate of change of sample temperature.

Another useful expression is the time τ required to reduce the initial surface concentration of a state of binding energy E by $1/e$ by heating at a temperature $T^\circ\text{K}$ and is

$$\tau = \nu^{-1} \exp\left(\frac{-E}{kT}\right)$$

with ν normally $= 10^{13} \text{ s}^{-1}$.

In Table II is shown values of τ for various binding energies between 0.9 eV and 2.8 eV and for temperatures of 200°C , 300°C and 400°C . For a value of the rate constant $\nu = 10^{12} \text{ s}^{-1}$, the times would, of course, be a factor of 10 higher. Such a value for ν

cannot be excluded.

The experimental equipment is shown schematically in Fig. 20 and a complete description will be found in the publication of Mathewson et al. [15].

Three types of stainless steel, all cleaned by the chemical solvent method described above, were investigated and in all three thermal diffusion of N_2 from the bulk tended to mask the thermal desorption spectra above about 600°C . The diffusion activation energy of this bulk N_2 was measured and found to be 1.87 eV (43 kcal mol.⁻¹) a value which corresponds closely to the quoted N_2 migration activation energy in austenitic Fe of 1.75 eV (40.3 kcal mol.⁻¹). (Smithells [16]).

In Fig. 21 is shown the flash desorption spectrum of CO from non-degassed 316 L + N stainless steel. Three desorption peaks are visible in the first flash, i.e. α , β and γ at 110, 395 and 517°C with corresponding binding energies of 0.97, 1.72 and 2.05 eV. The bulk N_2 diffusion is evident at the higher temperatures. Subsequent flashes revealed that α , β and γ states had been depleted but the bulk N_2 diffusion remained.

This clean sample was exposed to 10^{-6} torr of CO for increasing lengths of time and the spectra shown in Fig. 21 recorded. Only the α and γ states repopulated with CO even after 9.9×10^3 L (1L = 10^{-6} torr s) of exposure to CO.

Not all samples of the same stainless steel gave identical spectra, the peak positions varying somewhat from sample to sample. However, in Table III is a list of the positively identified CO binding state energies for the four stainless steel samples studied. The 2.8 eV state on 316 L is marked with a question mark since the exact peak position was difficult to determine due to the large N_2 background.

Baking at 300°C for 24 hours is insufficient to deplete all the CO binding states observed. In Table III it can be seen that at 300°C states with binding energies greater than about 1.7 eV are not depleted. This figure may be even less if the rate constant is lower than 10^{13} s^{-1} . Even at 400°C the 2.0 eV state may remain populated if the rate constant is 10^{12} s^{-1} . Thus even after 400°C bakeouts there will still be CO on the surface which may subsequently desorb under ion bombardment.

ACKNOWLEDGEMENTS

The author is indebted to Drs. Fischer, Calder, Blechschmidt and Hilleret for useful discussion, to Mlle. Achard for collaboration during the experimental measurements and to Mr. Grillot for valuable technical assistance.

REFERENCES

- [1] CALDER, R.S. "Ion Induced Gas Desorption Problems in the ISR", Vacuum 24, (10) pp. 437-443, 1974.
- [2] ALLEN, F.G., EISINGER, J., HAGSTRUM, H. and LAW, J.T., "Cleaning of Silicon Surfaces by Heating in High Vacuum", J. Appl. Phys. 30, (10), pp. 1563-1571, 1959.
- [3] PALMBERG, P.W., BOHN, G.K. and TRACY, J.C., "High Sensitivity Electron Spectrometer", Appl. Phys. Lett., 15, (8), pp. 254-255, 1969.
- [4] PALMBERG, P.W., RIACH, G.E., WEBER, R.E. and McDONALD, N.C., Handbook of Auger Electron Spectroscopy, Physical Electronics Industries Inc., Edina, MN, 1972.
- [5] ACHARD, MARIE-HELENE, Private Communication, in the form of a CERN internal report, CERN-ISR-VA/76-34.
- [6] MATHEWSON, A.G., Private Communication in the form of a CERN internal report, CERN-ISR-VA/76-5.
- [7] BARTON, R.S. and GOVIER, R.P., "The Effect of Cleaning Technique on the Outgassing Rate of 18/9/1 Stainless Steel", Vacuum 20, pp. 1-6, 1970.
- [8] HAAS, T.W., GRANT, J.T. and DOOLEY III, G.J., "Chemical Effects in Auger Electron Spectroscopy", J. Appl. Phys., 43, (4), pp. 1853-1860, 1972.
- [9] ACHARD, MARIE-HELENE and MATHEWSON, A.G., Private Communication in the form of a CERN internal report, CERN-ISR-VA/76-33.
- [10] MATHEWSON, A.G., Private Communication in the form of a CERN internal report, CERN-ISR-VA/74-13.
- [11] CARTER, G. and COLLIGON, J.S., "Ion Bombardment of Solids", Elsevier Publishing Co. Inc., New York, 1968.
- [12] LAMBERT, R.M. and COMRIE, C.M., "A Convenient Electrical Discharge Method for Eliminating Hydrocarbon Contamination from Stainless Steel UHV Systems", J. Vac. Sci. Technol., 11, (2), pp. 530-531, 1974.
- [13] CALDER, R.S., GRILLOT, A., MATHEWSON, A.G. and LE NORMAND, F., Private Communication.
- [14] REDHEAD, P.A., "Thermal Desorption of Gases", Vacuum, 12, pp. 203-210, 1962.
- [15] MATHEWSON, A.G., VERBEEK, P., GRILLOT, A. and CALDER, R.S., Private Communication in the form of a CERN internal report, CERN-ISR-VA/76-27.
- [16] SMITHELLS, C.J., Metals Reference Handbook, Vol. II, Butterworths, London, pp. 66, 1962.

TABLE I

The relative efficiencies of the ion induced desorption coefficient η_{K^+} and the electron induced desorption coefficient η_{e^-} at 1.4 keV for 316 L + N stainless steel, OFHC copper and pure Ti before and after 300°C, 24 hour bakeout.

gas desorbed	$\left(\frac{\eta_{K^+}}{\eta_{e^-}}\right)_{1.4 \text{ keV}}$ before bakeout			$\left(\frac{\eta_{K^+}}{\eta_{e^-}}\right)_{1.4 \text{ keV}}$ after bakeout at 300°C for 24 hours		
	316 L + N stainless steel	OFHC copper	pure titanium	316 L + N stainless steel	OFHC copper	pure titanium
H ₂	14	15	15	47	37	37
CH ₄	5	11	9	33	40	46
CO	14.5	23	17	120	150	130
CO ₂	3	4	2	7	7	7

TABLE II

The time τ in seconds required to reduce the initial surface concentration of a state of binding energy $E(\text{eV})$ by $1/e$ by heating at 200°C , 300°C and 400°C .

E(ev)	T ^{°C}	$\tau(\text{second})$		
	200	300	400	
0.9	3.8×10^{-4}	8.1×10^{-6}	5.4×10^{-7}	
1.7	1.2×10^5	8.6×10^1	5.2×10^1	
2.0	1.9×10^8	3.7×10^4	9.1×10^1	
2.8	6.4×10^{16}	4.0×10^{11}	8.8×10^7	

TABLE III

The positively identified CO binding state energies for four stainless steels. The 2.8 eV state on 316 L stainless steel is marked with a question mark since the exact peak position was difficult to ascertain due to the large N₂ background.

	316 L + N non-degassed	316 L + N degassed	316 L	NS 21
α -CO	0.97		1.2	$\approx$ 0.9
β -CO	1.72	1.67	1.7	1.55
γ -CO	2.05	1.91	2.2	1.96
δ -CO ?			2.8	
H ₂				0.89

TEXT TO THE FIGURES

- 1) Schematic diagram of the ion desorption equipment.
- 2) Scanning electron micrographs of Inconel 600, Inconel 625, 316 L + N stainless steel before and after degassing at 950°C in vacuo, glass bead vapour blasted Inconel 625 and "cleaned" Antico 100.
- 3) Auger spectra of 316 L + N stainless steel in the as received state, after only vapour degreasing, after the complete CERN precleaning procedure and after rinsing in ordinary tap water.
- 4) Auger spectra of Inconel 600 as a function of temperature.
- 5) The surface composition in atomic % of Inconel 600 as a function of temperature.
- 6) The $^{15}\text{N}_2^+$ ion induced desorption coefficient for Ti alloy after baking at 300°C for 6, 12, 18 and 24 hours.
- 7) The $^{15}\text{N}_2^+$ ion induced desorption coefficient for Ti alloy after baking at 200°C for 6, 12, 18 and 24 hours.
- 8) The desorption coefficient η as a function of incident ion energy.
- 9) The electron and K^+ ion induced desorption coefficients for OFHC Cu after precleaning and after 24 hours at 300°C.
- 10) Schematic diagram of the miniature discharge cell mounted in the Auger system.
- 11) Auger spectra from 316 L + N stainless steel before and after pure argon discharge.
- 12) Auger spectra from 316 L + N stainless steel before and after argon/10% oxygen discharge.
- 13) Schematic diagram of the discharge induced pressure bump analysis equipment.
- 14) A typical discharge induced pressure bump at 300°C.
- 15) The pressure bump from a previously discharged chamber after 4 weeks in air.
- 16) The $^{15}\text{N}_2^+$ ion induced desorption coefficient for Al after an in situ pure argon discharge.
- 17) The $^{15}\text{N}_2^+$ ion induced desorption coefficient for 316 L + N stainless steel after an in situ pure nitrogen discharge.
- 18) Auger spectra from 316 L + N stainless steel before and after in situ pure nitrogen discharge.
- 19) The electron and K^+ ion induced desorption coefficients for Al before and after an in situ pure argon discharge.
- 20) Schematic diagram of the flash desorption equipment.
- 21) The flash desorption spectrum of CO from non-degassed 316 L + N stainless steel.

FIGURE 1

Inconel 600

Inconel 625

316 L + N stainless steel
as received

316 L + N stainless steel
+ 950°C for 6 hours in vacuo

Antico 100
"cleaned"

Inconel 600
Glass bead blasted

Figure 2

FIGURE 3

FIGURE 4

FIGURE 5

FIGURE 6

65221

FIGURE 7

FIGURE 8

FIGURE 9

FIGURE 10

66534

FIGURE 11

66533

FIGURE 12

66535

FIGURE 13

FIGURE 16

FIGURE 17

FIGURE 18

FIGURE 19

FIGURE 20

66527

316L+N
NON DEGASSED

FIGURE 21

66528