The Compact Muon Solenoid Experiment

CMS Note

Mailing address: CMS CERN, CH-1211 GENEVA 23, Switzerland

RADIATION DAMAGE IN SCINTILLATING CRYSTALS¹⁾

Ren-yuan Zhu

California Institute of Technology, Pasadena, CA 91125, USA

Abstract

Crystal Calorimetry in future high energy physics experiments faces a new challenge to maintain its precision in a hostile radiation environment. This paper discusses the effects of radiation damage in scintillating crystals, and concludes that the predominant radiation damage effect in crystal scintillators is the radiation induced absorption, or color center formation, not the loss of scintillation light yield. The importance of maintaining crystal's light response uniformity and the feasibility to build a precision crystal calorimeter under radiation are elaborated. The mechanism of radiation damage in scintillating crystals is also discussed. While the damage in alkali halides is found to be caused by the oxygen/hydroxyl contamination, it is the structure defects, such as oxygen vacancies, cause damage in oxides. Material analysis methods used to reach these conclusions are presented in details.

¹⁾ Invited talks presented in “*International Conference on Inorganic Scintillators and Their Applications*”, Shanghai, Sept. 1997 and “*VII International Conference on Calorimetry in High Energy Physics*”, Tucson, Nov. 1997.

1 Introduction

Total absorption shower counters made of inorganic scintillating crystals have been known for decades for their superb energy resolution and detection efficiency. In high energy and nuclear physics, large arrays of scintillating crystals have been assembled for precision measurements of photons and electrons. The discovery potential of crystal calorimetry was early demonstrated by the Crystal Ball detector [1] through its study of radiative transitions and decays of the Charmonium family [2]. Over the last decade, following the Crystal Ball and CUSB [3] experiments, larger crystal calorimeters have been constructed, and their use has been a key factor in the successful physics programs of the L3 at LEP [4], of the CLEO II at CESR [5], and of the Crystal Barrel at LEAR [6].

Recently, several crystal calorimeters have been designed and are under development for the next generation of high energy physics experiment. These include a CsI calorimeter for the KTeV experiment at Fermi Lab [7], two CsI(Tl) calorimeters for B Factory experiments: the *BaBar* experiment at SLAC [8] and the BELLE experiment at KEK [9], and a lead tungstate (PbWO_4) calorimeter for the Compact Muon Solenoid (CMS) experiment at the Large Hadronic Collider (LHC) [10], where the electroweak symmetry breaking physics requires resolution of the crystal calorimetry [11]. Table 1 summarizes design parameters for these crystal calorimeters. One notes that each of these calorimeters requires several cubic meters of high quality crystals.

Table 1: Parameters of Recently Designed Crystal Calorimeters

Experiment	KTeV	<i>BaBar</i>	BELLE	CMS
Laboratory	FNAL	SLAC	KEK	CERN
Crystal Type	CsI	CsI(Tl)	CsI(Tl)	PbWO_4
B-Field (T)	-	1.5	1.0	4.0
Inner Radius (m)	-	1.0	1.25	1.29
Number of Crystals	3,300	6,580	8,800	83,300
Crystal Depth (X_0)	27	16 to 17.5	16.2	25
Crystal Volume (m^3)	2	5.9	9.5	11
Light Output (p.e./MeV)	40	5,000	5,000	2
Photosensor	PMT	Si PD	Si PD	APD ^a
Gain of Photosensor	4,000	1	1	50
Noise per Channel (MeV)	small	0.15	0.2	30
Dynamic Range	10^4	10^4	10^4	10^5

a Avalanche photodiode.

The unique physics capability of the crystal calorimetry is the result of its superb energy resolution, hermetic coverage and fine granularity [12]. In future high energy experiments, however, crystal calorimetry faces a new challenge: the radiation damage caused by the increased center of mass energy and luminosity. While the dose rate is expected to be a few rad per day for CsI(Tl) crystals at two B Factories, it would reach 15 to 500 rad per hour for PbWO_4 crystals at LHC.

This paper discusses effects of radiation damage in scintillating crystals, several importance issues related to the precision of a crystal calorimeter in radiation, and the cause and cure of the radiation damage in crystals. Section 2 gives a brief description of crystal scintillators commonly used in high energy and nuclear physics experiment. The radiation damage phenomena is discussed in Section 3 with particular emphasis given to the light response uniformity which is the key issue for achieving and preserving crystal precision *in situ*. Section 4 discusses the damage mechanism for alkali halides, such as BaF_2 and CsI. Section 5 addresses the oxides, such as bithmuth gemanade ($\text{Bi}_4\text{Ge}_3\text{O}_{12}$, BGO) and PbWO_4 . Finally, a summary is given in Section 6.

All measurements, except specified otherwise in the text, were carried out at Caltech with samples from Beijing Glass Research Institute (BGRI) in Beijing [13], Bogoroditsk Techno-Chemical Plant (BTCF) in Russia [14], Crismatec in France [15], Hilger in Margate, UK [16], Amcrys-H in Khar'kov, Ukraine [17] and Shanghai Institute of Ceramics (SIC) in Shanghai [18].

2 Commonly Used Crystal Scintillators

Table 2 lists the basic properties of some heavy crystal scintillators: NaI(Tl), CsI(Tl), undoped CsI, BaF_2 , BGO and PbWO_4 . All these crystals have been used in high energy and nuclear physics experiments, and are available

in large quantity. The CsI(Tl) crystal is known to have high light yield, and is widely used. Its photon yield per MeV energy deposition exceeds that of NaI(Tl). The relative light yield of 45% listed in the table is due to the quantum efficiency of the Bi-alkali cathode at its emission peak (7%), which is about 1/3, as compared to 20% of NaI(Tl). The PbWO₄ crystal is distinguished with its high density and small radiation length and Moliere radius, so was chosen by the CMS experiment to construct a compact crystal calorimeter. The low light yield of PbWO₄ can be overcome by gains of the photo-detector, such as the PMT and avalanche photodiode (APD).

Table 2: Properties of Some Heavy Crystal Scintillators

Crystal	NaI(Tl)	CsI(Tl)	CsI	BaF ₂	BGO	PbWO ₄
Density (g/cm ³)	3.67	4.51	4.51	4.89	7.13	8.3
Melting Point (°C)	651	621	621	1280	1050	1123
Radiation Length (cm)	2.59	1.85	1.85	2.06	1.12	0.9
Moliere Radius (cm)	4.8	3.5	3.5	3.4	2.3	2.0
Interaction Length (cm)	41.4	37.0	37.0	29.9	21.8	18
Refractive Index ^a	1.85	1.79	1.95	1.50	2.15	2.2
Hygroscopicity	Yes	slight	slight	No	No	No
Luminescence ^b (nm)	410	560	420	300	480	500
(at Peak)			310	220		500
Decay Time ^b (ns)	230	1300	35	630	300	50
			6	0.9		10
Light Yield ^{b,c}	100	45	5.6	21	9	0.3
			2.3	2.7		0.4
d(LY)/dT ^{b,d} (%/°C)	~0	0.3	-0.6	-2	-1.6	-1.9
				~0		

a At the wavelength of the emission maximum.

b Top line: slow component, bottom line: fast component.

c Relative and measured with a PMT with a Bi-alkali cathode.

d At room temperature.

3 Radiation Damage in Scintillating Crystals

All known crystal scintillators suffer from radiation damage. The most common damage phenomenon is the appearance of radiation-induced absorption bands caused by color center formation. The absorption bands reduce crystal's light attenuation length (LAL), and hence the light output. The color center formation, however, may or may not cause a degradation of the **light response uniformity**. The radiation also causes phosphorescence (after-glow), which leads to an increase of readout noise. Additional effect may include a reduced intrinsic scintillation light yield (damage of the scintillation mechanism), which would lead to a reduced light output and a deformation of the light response uniformity. The damage may recover under room temperature, which leads to the **dose rate dependence** [19]. Finally, thermal annealing and optical bleaching may be effective in eliminating color centers in the crystal.

In previous studies, we conclude that the scintillation mechanism of BGO [20], BaF₂ [21], CsI(Tl) [22] and PbWO₄ [23] are not damaged, and the consequence of the radiation-induced phosphorescence is negligible for BaF₂ [21] and PbWO₄ [24]. It is also known that the damage in BGO [20], BaF₂ [21] and PbWO₄ [24] are thermally annealable, as well as optically bleach-able, while it is not in CsI [22]. Because of the scope limit of this report, our discussion is concentrated on the main consequence of the radiation damage: the radiation-induced absorption.

3.1 Radiation-Induced Absorption

The most common damage in scintillating crystals is the radiation-induced color center formation, which reduces the light attenuation length and thus the light output. Depending on the type of the defects in the crystal, the color centers may be electrons located in anion vacancies (F center), or holes located in cation vacancies (V center), or interstitial anion atoms (H center) or ions (I center). Radiation-induced color centers may be observed by measurement of crystal's transmittance. The left side of Figure 1 shows the longitudinal transmittance of three full size (~30 cm long) CsI(Tl) samples [22]. The radiation-induced absorption bands are clearly identified in samples BGRI-2 and SIC-4, but is not seen in sample SIC-5, which was grown with a special scavenger in the melt to remove the oxygen contamination. The distinguished absorption bands centered at 850, 560, 520 and 440 nm are

commonly attributed to F, F', F'' and F''' centers, respectively. The right side of Figure 1 shows the longitudinal transmittance of four large size (~ 20 cm long) PbWO_4 samples [23]. The radiation-induced absorption bands in PbWO_4 are broad, and can be seen in all four samples BTCP-767, 1015, 1018 and SIC-66. A more detailed discussion of color centers can be found in references [25].

Figure 1: Longitudinal transmittance of CsI(Tl) (left) and PbWO_4 (right) samples, showing radiation-induced absorption bands.

3.2 Light Response Uniformity

An adequate light response uniformity profile is the key to the precision of a crystal calorimeter. The effect of the light response uniformity to the energy resolution has been studied by full GEANT simulations for each designed crystal calorimeter. The left side of Figure 2 [21] shows a GEANT prediction for the energy fraction (top figure) and the intrinsic energy resolution (bottom figure) calculated by summing the energies deposited in a 3×3 sub-array, consisting of tapered BaF_2 crystals of 25 radiation length, as a function of the light response uniformity. In this simulation, the light response (y) of the crystal was parametrized as a normalized linear function:

$$\frac{y}{y_{mid}} = 1 + \delta(x/x_{mid} - 1), \quad (1)$$

where y_{mid} represents the light response at the middle of the crystal, δ represents the deviation of the light response uniformity, and x is the distance from the small (front) end of a tapered crystal. The right side of Figure 2 shows the definition of the light response uniformity in this simulation and a schematic illustrating its measurement in laboratory by shooting a point γ -ray source at difference locations of a tapered crystal.

While the degradation of the amplitude of the light output can be inter-calibrated, the loss of the energy resolution, caused by the degradation of light response uniformity is not recoverable. To preserve crystal's intrinsic energy resolution the light response uniformity thus must be kept within tolerance. According to the above simulation, the δ value is required to be less than 5% so that its contribution to the constant term of the energy resolution is less than 0.5%. Other detailed studies, such as a simulation for BaF_2 crystals using many different functional forms of the light response nonuniformity [26] and a recent simulation for CMS PbWO_4 crystals [27], confirmed this conclusion.

Because of the non-uniform dose profile in crystals, caused by energy deposition of particles in experiment, a damage to the scintillation mechanism would cause a distortion of the light response uniformity and thus unrecoverable degradation of the energy resolution. The radiation-induced absorption, however, may or may not cause a severe distortion of the light response uniformity.

Figure 2: Left: The effect of light response uniformity predicted by a GEANT simulation. Right: A schematic showing the light response uniformity definition and its laboratory measurement.

Figure 3 shows the light response uniformity as a function of accumulated dose for full size CsI(Tl) (~ 30 cm, left) and PbWO₄ (~ 20 cm, right) crystals. The pulse heights measured in nine points evenly distributed along the longitudinal axis of the crystal is fit to Equation 1. This figure shows clearly that the slope (δ) does not change up to 10 krad for the CsI(Tl) sample and to 2.2 Mrad for the PbWO₄ sample. The result of CsI(Tl) sample confirms that the CsI(Tl) scintillation mechanism is not damaged, since only the front few cm of the sample was subject to the radiation dose in this experiment, where a high intensity ⁶⁰Co source was used to illuminate the front face of the crystal. Although the PbWO₄ sample was subject to a uniform irradiation, an experiment of irradiating only the middle 10 cm of a PbWO₄ crystal led to the same result, confirming that the PbWO₄ scintillation mechanism is also not damaged. These two samples are example of crystals of good quality. The light response uniformity profile does change under irradiation for crystals of poor quality [22, 23]. The result of this laboratory measurement was later confirmed by a beam test for a PbWO₄ crystal array at CERN. Intensive electron beam was used to irradiate crystals, and no degradation of energy resolution was found for a sample SIC 69 before and after beam irradiation with an integrated dose of 650 rad [28].

These results is understood by a detailed ray-tracing simulation, as the intensity of all light rays attenuates similarly after passing the same radiation-induced absorption zone in the crystal. The exact geometry of a full size PbWO₄ crystal ($2^2 \times 23 \times 2.3^2$ cm) was used in this simulation. The refractive index of PbWO₄ [29] was assumed to be a tensor, and the polarization of the light ray is taken into account. The simulation was carried out for two photo-detectors: a PMT and an APD. While the PMT covers the full back face of the crystal, only 3.7% of the back area of the crystal was covered by the APD of $\phi 5$ mm diameter. The optical coupling between photo-detectors and the crystal was assumed to have a refractive index of 1.5. The crystal was assumed to be wrapped with Tyvek paper for all surfaces except the part covered by the detector. The interface between Tyvek paper and crystal surface was assumed to have a thin air gap and a reflectivity of 0.9, and a defused reflection with the reflection angle smeared with a Gaussian width of 0.5 radian. Photons were generated isotropically in the crystal and were traced all the way. The cumulated path length of the photon was used together with the assumed light attenuation length to calculate the weight of the photon. Photons were followed until either absorbed by the photo-detector or escaped from the crystal, or its weight is less than e^{-5} . Finally, the light collection efficiency (η) was obtained by averaging all weights of photons absorbed by the photo-detector, and was fitted to the Equation 1.

Table 3 lists the numerical result together with statistical errors of the simulation. As can be seen from this table, the slope of the light response uniformity (δ) is entirely determined by the crystal geometry, if the light attenuation length is long enough. The table also shows that the light output (y_{mid}) of a detector covering a smaller fraction of the back face (APD) is more sensitive to the degradation of the light attenuation length, or radiation induced color centers.

Since the degradation of the amplitude of the light output can be inter-calibrated with physics events or by a

Figure 3: Left: The light response uniformities are shown as a function of integrated dose for full size CsI(Tl) (left) and PbWO₄ (right) samples.

Table 3: Result of a Ray-Tracing Simulation for a Full Size PbWO₄ Crystal

LAL (cm)	20	40	60	80	200	400
Full Face Photo-detector, Covering 100% Back Face						
y_{mid} (%)	9.5 ± 0.2	15.7 ± 0.4	19.2 ± 0.5	21.6 ± 0.6	26.9 ± 0.7	29.1 ± 0.8
δ (%)	23 ± 1	-5 ± 1	-11 ± 1	-15 ± 1	-15 ± 1	-16 ± 1
$\phi 5$ mm Photo-detector, Covering 3.7% Back Face						
y_{mid} (%)	$.38 \pm 0.04$	$.74 \pm 0.08$	1.1 ± 0.1	1.4 ± 0.2	3.0 ± 0.3	5.1 ± 0.3
δ (%)	23 ± 4	-4 ± 4	-12 ± 4	-16 ± 4	-17 ± 3	-16 ± 2
$\frac{y_{mid}(\phi 5mm)}{y_{mid}(Full)}$ (%)	4.0	4.7	5.7	6.5	11	17.5

light monitoring system, if it is caused by optical absorption, to preserve crystal precision *in situ* two necessary conditions must be satisfied. First, crystal's scintillation mechanism must not be damaged and second, crystal's initial light attenuation length must be long enough and the density of radiation-induced color center must be low enough, so that the light response uniformity does not degrade *in situ*.

3.3 Damage Recovery

The radiation damage in crystal may recover at room temperature — a consequence of room temperature thermal annealing. The recovery speed, however, depends on the depth of the traps. A slow recovery would ease the calibration requirement, so is preferred for crystals to be used in a radiation environment. It is known that damage in BaF₂ [21] and CsI [22] recovers at an extremely slow speed, while BGO [20] and PbWO₄ [24] do recover at a speed of orders of few hours to few weeks.

The left side of Figure 4 shows the recovery speed of less than 0.5% per day for three full size (~ 30 cm) CsI(Tl) samples after a 100 krad irradiation, which indicates that the radiation-induced color centers in CsI(Tl) are caused by deep traps. The thermal annealing did not accelerate the recovery when below 300°C, and made sample BGRI-2 turned milky and produced no more scintillation light when beyond 300°C. This was explained by the drift of the thallium luminescence centers out of the CsI(Tl) lattice at 300°C. Because of this slow recovery, the required accuracy of inter-calibration may be provided by physics *in situ*, e.g. Bhabha events, in a few hours.

The right side of Figure 4 shows the damage recovery for a full size (23 cm) PbWO₄ sample BTCP-1015 after a

Figure 4: The recovery of radiation damage is shown for three full size (~ 30 cm) CsI(Tl) crystals after 100 krad irradiation (left) and a full size (23 cm) PbWO₄ crystal after 1 Mrad irradiation (right).

dose of 1 Mrad. The top plot shows the recovery in the transmittance as a function of wavelength. The bottom plot shows normalized light output as a function of time after irradiation. The solid line in the light output plot is a fit to an exponential with a time constant of 160 hour. Because of this damage and recovery, special attention should be paid to the stability of a PbWO₄ calorimeter *in situ*.

3.4 Dose Rate Dependence

If both annihilation and creation coexist, the color center density at the equilibrium depends on the dose rate applied. Assuming the annihilation speed of color center i is proportional to a constant a_i and its creation speed is proportional to a constant b_i and the dose rate (R), the differential change of color center density when both processes coexist can be written as [30]:

$$dD = \sum_{i=1}^n \{-a_i D_i + (D_i^{all} - D_i) b_i R\} dt, \quad (2)$$

where D_i is the density of the color center i in the crystal and the summation goes through all centers. The solution of Equation 2 is

$$D = \sum_{i=1}^n \left\{ \frac{b_i R D_i^{all}}{a_i + b_i R} [1 - e^{-(a_i + b_i R)t}] + D_i^0 e^{-(a_i + b_i R)t} \right\}, \quad (3)$$

where D_i^{all} is the total density of the trap related to the center i and D_i^0 is its initial density. The color center density in equilibrium (D_{eq}) thus depends on the dose rate (R).

$$D_{eq} = \sum_{i=1}^n \frac{b_i R D_i^{all}}{a_i + b_i R}, \quad (4)$$

The left side of Figure 5 shows the entire history of a light output measurement for a 5 cm PbWO₄ sample SIC 115-1 in 20 days. The measured light output was normalized to that before irradiation, and was plotted as a function of the time of the measurement. The dose rate and integrated dose are also shown in the figure. There were periods when dose rate was shown as zero, indicating a recovery test. As shown in the figure, the level of PbWO₄ damage is indeed dose rate dependent, and the fast recovery (in order of a few hours) was observed only when dose rate is 15.7 krad/h, as shown in the insert.

Figure 5: The dose rate dependence is shown for a 5 cm PbWO_4 sample SIC 115-1 (left), and no dose rate dependence was observed for a 25 cm BaF_2 sample (right).

If the recovery speed (α) is slow, however, the dose rate dependence would be less important, the color center density in the equilibrium would less depends on the dose rate. The extrema is no dose rate dependence, as shown in Equation 5

$$D'_{eq} = \sum_{i=1}^n D_i^{all}. \quad (5)$$

The right side of Figure 5 [21] shows the transmittance as a function of wavelength for a full size (25 cm) BaF_2 sample before and after 100, 1k, 10k, 100k and 1M rad irradiations (from top to bottom) under a fast (a) and a slow (b) dose rate. While the fast rate is up to a factor of three higher than the slow rate, the damage levels for the same integrated dose are identical. This was expected, since no recovery at room temperature was observed for BaF_2 . Because of this dose rate dependence, an adequate rad-hard specification for PbWO_4 crystals would refer to a level of light output degradation under a specific dose rate expected at LHC of full luminosity.

4 Damage Mechanism in Alkali Halides

Material analysis is very important in identifying the radiation damage mechanism. We tried the Glow Discharge Mass Spectroscopy (GDMS) analysis in Charles Evans & Associates [31], looking for correlations between the trace impurities in the CsI(Tl) crystals and their radiation hardness. Samples were taken 3 to 5 mm below the surface of the crystal to avoid surface contamination. A survey of 76 elements, including all of the lanthanides, indicates that there are no obvious correlations between the detected trace impurities and crystal's susceptibility to the radiation damage. This indicates an important role of oxygen contamination which can not be determined by GDMS.

The oxygen contamination is known to cause radiation damage in alkali halide scintillators. In BaF_2 [21], for example, hydroxyl (OH^-) may be introduced into crystal through a hydrolysis process, and latter decomposed to interstitial and substitutional centers by radiation through a radiolysis process. Equation 6 shows a scenario of this process:

where subscript i and s refer to interstitial and substitutional centers respectively. Both the O_s^- center and the U center (H_s^-) were identified [21].

Following the BaF_2 experience, effort was made to remove oxygen contamination in CsI(Tl) crystals. An approach was taken at SIC: using a scavenger, such as Pb for BaF_2 , to remove oxygen contamination. A significant

improvement of the radiation hardness was achieved for CsI(Tl) crystals produced taking this approach [22]. The left side of Figure 6 shows the light output as a function of accumulated dose for full size CsI(Tl) samples, and compared to the *BaBar* radiation hardness specification (solid line). While the late samples SIC-5, 6, 7 and 8 (with scavenger) satisfy the *BaBar* specification, early samples SIC-2 and 4 did not. It is understood that the function of the scavenger is to form oxide with density less than CsI, so that the oxide will migrate to the top of the ingot during the growing process, similar to the zone-refining process. By doing so, both oxygen and scavenger are removed from the crystal.

Figure 6: Left: The progress of CsI(Tl) radiation hardness is shown for full size (~ 30 cm) CsI(Tl) samples from SIC together with the rad-hard specification of *BaBar* experiment. Right: The depth profile of oxygen contamination is shown for two rad-soft CsI(Tl) samples (SIC-T1 and SIC-2) and two rad-hard samples (SIC-T3 and Khar'kov).

Additional analysis was carried out to quantitatively identify the oxygen contamination in CsI(Tl) samples. We first tried the Gas Fusion (LECO) at Shiva Technologies West, Inc. [32], and found that the oxygen contamination in all CsI(Tl) samples is below the LECO detection limit: 50 ppm. We then tried Secondary Ionization Mass Spectroscopy (SIMS) at Charles Evans & Associates. A Cs ion beam of 6 keV and 50 nA was used to bombard the CsI(Tl) sample. All samples were freshly cleaved prior before being loaded to the UHV chamber. An area of 0.15×0.15 mm² on the cleaved surface was analyzed. To further avoid surface contamination, the starting point of the analysis is at about 10 μ m deep inside the fresh cleaved surface. The right side of Figure 6 shows depth profile of oxygen contamination for two rad-soft (SIC-T1 and SIC-2) and two rad-hard (SIC-T3 and Khar'kov) CsI(Tl) samples. Crystals with poor radiation resistance have oxygen contamination of 10^{18} atoms/cm³ or 5.7 ppmW, which is 5 times higher than the background count (2×10^{17} atoms/cm³, or 1.4 ppmw). The radiation damage in CsI(Tl) is indeed caused by oxygen contamination.

5 Damage Mechanism in Oxides

Similarly, the GDMS analysis at Charles Evans & Associated found no specific correlations between the detected trace impurities in PbWO₄ crystals and crystal's susceptibility to the radiation damage [24]. This indicates an important role of defects in the crystal, such as oxygen vacancies which can not be determined by GDMS. Table 4 lists result of GDMS analysis for trace elements (ppmw) in several PbWO₄ samples.

The result of GDMS analysis, however, revealed that the slow scintillation component in PbWO₄ is caused the Mo contamination, as shown in the left side of Figure 7. A similar observation was early reported by M. Kobayashi [33]. This correlation is easy to be understood, since lead molybdate (PbMoO₄) is a known scintillators with slow (~ 10 μ s) decay time. After removing Mo and other cation contamination from the raw material, PbWO₄ crystals produced at both BTCP and SIC have a significantly reduced slow component.

Table 4: Result of GDMS Trace Analysis (ppmw) for PbWO_4 Samples

Element	Na	Si	K	Ca	Nb	Mo	Ba	TM ^a	RE ^b
BTCP-478	1.8	3.0	2.5	1.3	2.4	4.6	0.24	1.2	0.13
BTCP-728	3.2	<0.7	<0.3	5.5	3.9	8.9	0.82	<1.0	0.28
BTCP-767	9.3	42	0.52	0.97	7.8	16	0.40	<0.4	0.11
BTCP-768	1.8	51	0.52	2.4	6.9	15	0.51	<0.4	0.12
BTCP-1015	2.8	1.5	1.9	5.5	7.9	120	0.16	1.8	0.11
BTCP-1022	3.1	1.8	1.7	7.7	10	100	0.16	1.6	0.10
SIC-34	3.0	1.3	3.3	2.7	<.002	14	1.0	1.3	0.18
SIC-41	1.7	0.8	3.4	10	<.001	18	3.8	1.4	0.15
SIC-O1	0.5	0.4	0.5	0.4	<.05	1.1	0.02	.02	<0.05
SIC-O2	0.1	0.02	0.2	0.2	<.05	0.6	0.03	.06	<0.05

a. Sum of transition metals.

b. Sum of rare earths.

Figure 7: Left: The correlation between Mo contamination and the fraction of fast scintillation component. Right: Radiation-induced absorption spectra of four doped BGO samples ($1 \times 3 \times 1$ cm) are decomposed to three common absorption bands.

Crystal defects, such as oxygen vacancies, is known to cause radiation damage in oxide scintillators. In BGO, for example, three common radiation induced absorption bands at 2.3, 3.0 and 3.8 eV were found in a series of 24 doped samples [20], indicating defect-related color centers, such as oxygen vacancies. The right side of Figure 7 shows the radiation induced absorption spectra for four small ($1 \times 3 \times 1$ cm) BGO samples doped with Ca, Mn, Pb and Cr, respectively. Although the shape of these radiation-induced absorption bands are rather different, a decomposition showed three common absorption bands at the same energy and with the same width.

Following the BGO experience, effort was made to reduce oxygen vacancies in PbWO_4 crystals. An approach was taken at SIC: oxygen compensation through post-growth thermal annealing in an oxygen-rich atmosphere. Significant improvement of radiation hardness was achieved. The left side of Figure 8 shows the normalized light output at the equilibrium as a function of the dose rate for 6 pairs of small ($2 \times 5 \times 2$) PbWO_4 samples, which were treated with different oxygen compensation conditions. The result shows that samples annealed under different conditions have much different behavior. Samples, which were not annealed, have the worst radiation hardness. Samples annealed in oxygen is more radiation hard than that in air. Samples, which were annealed under the optimized oxygen conditions, are the best.

Figure 8: Left: Normalized light output at the equilibrium is shown as a function of the dose rate for six pairs of small ($2 \times 5 \times 2$ cm) PbWO_4 samples treated with different post-growing thermal annealing conditions. Right: The normalized light output of a small ($2 \times 5 \times 2$ cm) PbWO_4 sample SIC 153 is shown as a function of the integrated dose.

Samples treated under the optimized oxygen annealing are radiation hard. The right side of Figure 8 shows the normalized light output as a function of integrated dose up to 20 Mrad for a small ($2 \times 5 \times 2$) sample 153. This sample showed no degradation in light output under a dose rate of below 480 rad/h, and had only 2% degradation under an extremely high dose rate of 15.7 krad/h. Samples of this quality certainly can satisfy the most stringent radiation hardness specification for CMS.

Further analysis was carried out to quantitatively identify the stoichiometry deviation and oxygen vacancies in PbWO_4 samples. We first tried Particle Induced X-ray Emission (PIXE) and quantitative wavelength dispersive Electron Micro-Probe Analysis (EMPA) for PbWO_4 crystals in Charles Evans & Associates. Indeed, crystals with poor radiation hardness were found to have a non-stoichiometric W/Pb ratio [24]. However, both PIXE and EMPA did not provide oxygen analysis.

The direct observation of oxygen vacancies requires a measurement of the complete stoichiometric ratio of Pb:W:O in PbWO_4 samples. X-ray Photoelectron Spectroscopy (XPS) was tried at Charles Evans & Associates [34]. It, however, was found to be very difficult due to the systematic uncertainty in oxygen analysis. Effort has also been made to directly identify oxygen vacancies by Electron Paramagnetic Resonance (ESR) and Electron-Nuclear Double Resonance (ENDOR) through observing unpaired electrons. It, however, was also difficult to reach a quantitative conclusion.

By using Transmission Electron Microscopy (TEM) coupled to Energy Dispersion Spectrometry (EDS), a localized stoichiometry analysis was possible to identify oxygen vacancies. A TOPCON-002B Scope was first used at 200 kV and 10 μA . Samples were made to powders of an average grain size of a few μm , and then placed on a sustaining membrane. With a spatial resolution of 2 $\text{\AA}$, the lattice structure of PbWO_4 crystals was clearly visible. The left side of Figure 9 shows a TEM picture taken for a sample with poor radiation hardness. Black spots of a diameter of 5 – 10 nm were clearly seen in the picture. On the other hand, samples with good radiation hardness show stable TEM picture with no black spots, as shown in the right side of Figure 9.

By employing a TEM with EDS system, a localized stoichiometry analysis was carried out at SIC [35]. The system is a JEOL JEM-2010 scope and a Link ISIS EDS. The spatial resolution of this system allows a localized stoichiometry analysis in a region of a diameter of 0.5 nm [35]. An as grown sample was first analyzed, and black spots were observed. Points inside and surrounding the black spots were analyzed as well as points far away from

Figure 9: TEM pictures of a PbWO_4 crystal of poor (left) radiation hardness, showing clearly the black spots of $\phi 5\text{--}10\text{ nm}$ related to oxygen vacancies, as compared to that of a good one (right).

Table 5: Atomic Fraction (%) of O, W and Pb in PbWO_4 Samples Measured by TEM/EDS [35]

<u>As Grown Sample</u>				
Element	Black Spot	Peripheral	Matrix ₁	Matrix ₂
O	1.5	15.8	60.8	63.2
W	50.8	44.3	19.6	18.4
Pb	47.7	39.9	19.6	18.4

<u>The Same Sample after Oxygen Compensation</u>				
Element	Point ₁	Point ₂	Point ₃	Point ₄
O	59.0	66.4	57.4	66.7
W	21.0	16.5	21.3	16.8
Pb	20.0	17.1	21.3	16.5

the black spots. The uncertainty of the analysis is typically 15%. The resultant atomic fractions (%) at these areas are listed in Table 5. A clear deviation from the atomic stoichiometry of $\text{O}:\text{W}:\text{Pb} = 66:17:17$ was observed in the center of these black spots, pointing to a severe deficit of oxygen component. In the peripheral area, the oxygen deficit was less, but still significant. There was no oxygen deficit observed in the area far away from the black spots. As a comparison, the same sample after oxygen compensation was re-analyzed. No black spot was found. The result of the analysis is also listed in Table 5. In all randomly selected points no stoichiometry deviation was observed. This analysis thus clearly identified oxygen vacancies in PbWO_4 samples of poor radiation hardness.

6 Summary

Crystal calorimeters in future high energy colliders will operate in a severe radiation environment caused by the increased center of mass energy and luminosity. Despite much experience and expertise accumulated in the last decade, crystal calorimetry is facing a new challenge. Without stringent quality control, crystals would suffer from significant radiation damage, leading to a degraded performance.

Possible effects of radiation damage in scintillating crystals include (1) radiation induced absorption; (2) radiation induced phosphorescence, and maybe (3) damage in scintillation mechanism. The predominant radiation damage effect in crystal scintillators is the radiation induced absorption, or color center formation, not the loss of scintillation light yield. Table 6 summarizes radiation damage effect in commonly used crystal scintillators.

Table 6: Radiation Damage Effect in Crystal Scintillators

Crystal	CsI(Tl)	CsI	BaF ₂	BGO	PbWO ₄
Color Centers	Yes	Yes	Yes	Yes	Yes
Phosphorescence	Yes	Yes	Yes	Yes	Yes
Scintillation	No	No	No	No	No
Recover @Room Temperature	Slow	Slow	No	Yes	Yes
Dose Rate Dependence	No	No	No	Yes	Yes
Thermal Annealing	No	No	Yes	Yes	Yes
Optical Bleaching	No	No	Yes	Yes	Yes

It is understood that crystal scintillators for precision calorimetry must preserve their light response uniformity under irradiation, which requires a long enough initial light attenuation length and a low enough color center density. With such crystals, a precision light monitoring may function as inter-calibrations.

The radiation damage in alkali halides is understood to be caused by the oxygen and/or hydroxyl contamination, as evidenced by the SIMS analysis and the effectiveness of the usage of a scavenger in removing oxygen contamination in CsI(Tl) crystals. It is also understood that the stringent specifications for CsI(Tl) crystals to be used to construct calorimeters for two B Factories can be met by mass-produced crystals.

The radiation damage in oxides is understood to be caused by stoichiometry-related defects, e.g. oxygen vacancies, as evidenced by localized stoichiometry analysis by TEM/EDS, and the effectiveness of the oxygen compensation for PbWO₄ crystals. It is expected that rad-hard PbWO₄ crystals will be developed through the systematic research and development program carried out by CMS physicists in collaboration with crystal manufactures.

Acknowledgements

Measurements at Caltech were carried out by Mr. Q. Deng, H Wu, D.A. Ma, Z.Y. Wei and T.Q. Zhou. Part of the PbWO₄ related work was carried out by Dr. C. Woody and his group at Brookhaven National Laboratory. Prof. Z.W. Yin, Drs. G. Cheng and P. Lecoq provided samples described in this report. Many inspiring and interesting discussions with Drs. M. Kobayashi, P.J. Li, J.Y. Liao, D.Z. Shen, C. Woody, and Z.W. Yin are also acknowledged. The author would also like to thank Dr. J.L. Faure for reading and commenting the manuscript. This work is supported in part by U.S. Department of Energy Grant No. DE-FG03-92-ER40701.

References

- [1] M. Oreglia *et al.*, *Phys. Rev. D* **25** 2295 (1982).
- [2] E. Bloom and C. Peck, *Ann. Rev. Nucl. Part. Sci.* **33** 143 (1983).
- [3] T. Bringer *et al.*, *Phys. Rev. Lett.* **44** 1111 (1980); G. Mageras *et al.*, *Phys. Rev. Lett.* **46** 1115 (1981).
- [4] L3 Collaboration, *Nucl. Instr. and Meth.* **A289** 35 (1990).
- [5] Y. Kubota *et al.*, *Nucl. Instr. and Meth.* **A320** 66 (1992).
- [6] E. Aker *et al.*, *Nucl. Instr. and Meth.* **A321** 69 (1992).
- [7] K. Arisaka *et al.*, *KTeV Design Report*, **FN-580**, January (1992).
- [8] BaBar Collaboration, *Technical Design Report*, **SLAC-R-95-457** (1995).
- [9] BELLE Collaboration, *Technical Design Report*, **KEK Report 95-1** (1995).
- [10] CMS Collaboration, *The Electromagnetic Calorimeter Technical Design Report*, CERN/LHCC 97-33 (1997).

- [11] S. Mrenna *et al.*, **CALT 68-1856**, June 1993; R.Y. Zhu and H. Yamamoto, **CALT 68-1802**, July 1992; and R.Y. Zhu, **CALT 68-1777**, November 1991.
- [12] G. Gratta *et al.*, *Annu. Rev. Nucl. Part. Sci.* **44** 453 (1994).
- [13] Beijing Glass Research Institute is a research institution in Beijing, 1 Dongdadi Chongwenmen Wai, Beijing 100062, China.
- [14] Bogoroditsk Techno-Chemical Plant, Russia.
- [15] The Crismatec is a subsidiary of Saint-Gobain Ceramics Industries, 77794 Nemours Cedex, France.
- [16] The Hilger Analytical Limited is in Westwood, Margate, Kent CT9 4JL United Kingdom.
- [17] The Amcrys-H is the commercial branch of the Institute for Single Crystals Research, 60 Lenin Ave, Khar'kov, Ukraine.
- [18] Shanghai Institute of Ceramics is a research institution belong to the Chinese Academy of Sciences, 1295 Ding Xi Road, Shanghai 200050, China.
- [19] R.Y. Zhu, *IEEE Trans. Nucl. Sci.* **NS-44** 468 (1997).
- [20] R.Y. Zhu *et al.*, *Nucl. Instr. and Meth.* **A302** 69 (1991),
- [21] R.Y. Zhu, *Nucl. Instr. and Meth.* **A340** 442 (1994).
- [22] R.Y. Zhu *et al.*, in *Proc. of the 6th Int. Conf. on Calorimetry in High Energy Physics*, ed. A. Antonelli *et al.*, Frascati Physics Series 589 (1996).
- [23] R.Y. Zhu *et al.*, in *Proc. of the 6th Int. Conf. on Calorimetry in High Energy Physics*, ed. A. Antonelli *et al.*, Frascati Physics Series 577 (1996).
- [24] C. Woody *et al.*, in *Proceedings of SCINT95 Int'l Conf.* Delft, August 1995 and *IEEE-NUCL-S V43* (1996) 1585; R.Y. Zhu *et al.*, *Nucl. Instr. and Meth.* **A376** 319 (1996).
- [25] There are many literatures discussing color centers in solids, for example, J.H. Crawford and L.M. Slifkin, *Point Defects in Solids*, Plenum Press, New York (1972).
- [26] K. Shmakov, **GEM TN-92-143**, August (1992).
- [27] D. Graham and C. Seez, **CMS Note 1996-002**.
- [28] E. Auffray *et al.*, **CMS Note 97-099**, submitted to *Nucl. Instr. and Meth.*
- [29] G. Bakhshiva & A. Morozov, *Sov.J.Opt.Technol.* **44** (9), Sept, 1977.
- [30] D.A. Ma *et al.*, *Nucl. Instr. and Meth.* **A332** 113 (1993) and D.A. Ma *et al.*, *Nucl. Instr. and Meth.* **A356** 309 (1995).
- [31] Charles Evans & Associates, 301 Chesapeake Drive, Redwood City, CA 94063.
- [32] Shiva Technologies West, Inc., 16305 Caputo Drive Suite C, Morgan Hill, CA 95037.
- [33] M. Kobayashi *et al.*, *Nucl. Instr. and Meth.* **A373** (1996) 333.
- [34] C. Lazik, private communications.
- [35] Z.W. Yin *et al.*, paper in *Proceedings of SCINT97 Int'l Conf.*, Shanghai, September 1997.